Influence of water and humidity on chemically modifying wood with polybutylene succinate bio-polyester

Noel, M.; Grigsby, W.J.; Ormondroyd, Graham; Spear, Morwenna

International Wood Products Journal

DOI:

[10.1080/20426445.2016.1160559](https://doi.org/10.1080/20426445.2016.1160559)

Published: 01/06/2016

Peer reviewed version

[Cyswllt i'r cyhoeddiad / Link to publication](#)

Dyfyniad o'r fersiwn a gyhoeddwyd / Citation for published version (APA):

Noel, M., Grigsby, W. J., Ormondroyd, G., & Spear, M. (2016). Influence of water and humidity on chemically modifying wood with polybutylene succinate bio-polyester. *International Wood Products Journal*, 7(2), 80-88. <https://doi.org/10.1080/20426445.2016.1160559>

Hawliau Cyffredinol / General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal ?

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

International Wood Products Journal

Influence of water and humidity on chemically modifying wood with polybutylene succinate bio-polyester --Manuscript Draft--

Manuscript Number:	IWP239R1	
Full Title:	Influence of water and humidity on chemically modifying wood with polybutylene succinate bio-polyester	
Article Type:	Special Issue Article	
Keywords:	bio-polymer, dimensional stabilisation, poly(butylene succinate), poly(lactic acid), wood modification	
Corresponding Author:	Marion Noël Berne University of Applied Sciences SWITZERLAND	
Corresponding Author Secondary Information:		
Corresponding Author's Institution:	Berne University of Applied Sciences	
Corresponding Author's Secondary Institution:		
First Author:	Marion Noël	
First Author Secondary Information:		
Order of Authors:	Marion Noël	
	Warren J. Grigsby	
	Graham A. Ormondroyd	
	Morwenna J. Spear	
Order of Authors Secondary Information:		
Abstract:	This paper reports attempts to optimise the chemical modification of wood impregnated with polybutylene succinate oligomers (OBS). OBS impregnation at temperature and subsequent heating to induce in-situ polymerisation led to high OBS uptake, but limited dimensional stability. However, subsequent water soaking followed by drying enhances wood dimensional stability in both high humidity environments and in liquid water. To enhance OBS treatment and performance, it was found that OBS impregnation followed by wet heat or water soaking and a second heating step, promoted oligomer migration into wood cell walls. These combined treatments provided modified wood with anti-swelling efficiency at 95% relative humidity (ASE*95%RH) values of 55 to 70 %.	
Funding Information:	European Cooperation in Science and Technology (STSM-FP1303-100515-060044)	Dr. Marion Noël

Influence of water and humidity on chemically modifying wood with polybutylene succinate bio-polyester

Marion NOËL^{1,*}, Warren J. GRIGSBY², Graham A. ORMONDROYD^{3,4}, Morwenna J. SPEAR³

¹Department Wood, Architecture and Civil Engineering; Berne University of Applied Sciences, Solothurnstrasse 102, 2500 Biel, Switzerland [email: marion.noel@bfh.ch, +41.32.344.03.35]

²Scion, Private Bag 3020, Rotorua, New Zealand [email: warren.grigsby@scionresearch.com]

³BioComposites Centre, Bangor University, Bangor, Gwynedd LL57 2UW, UK [email: g.ormondroyd@bangor.ac.uk; m.j.spear@bangor.ac.uk]

⁴Department of Architecture and Civil Engineering, University of Bath, Claverton Down, Bath, BA2 7AY, UK

*Corresponding author

1. Abstract

This paper reports attempts to optimise the chemical modification of wood impregnated with polybutylene succinate oligomers (OBS). OBS impregnation at temperature and subsequent heating to induce *in-situ* polymerisation led to high OBS uptake, but limited dimensional stability. However, subsequent water soaking followed by drying enhances wood dimensional stability in both high humidity environments and in liquid water. To enhance OBS treatment and performance, it was found that OBS impregnation followed by wet heat or water soaking and a second heating step, promoted oligomer migration into wood cell walls. These combined treatments provided modified wood with anti-swelling efficiency at 95% relative humidity ($ASE_{95\%RH}^*$) values of 55 to 70 %.

Keywords: bio-polymers, dimensional stabilisation, poly(butylene succinate), poly(lactic acid), wood modification

2. Introduction

Enhancing the properties and performance of wood has been extensively studied over many decades. During this time, a range of wood treatments have been developed and commercialised to improve the strength, hardness and durability of treated woods (Hill 2006; Rowell 2005; Lande *et al.* 2004; Chang and Chang 2002; Ibach 2005; Xie *et al.* 2005; Belgacem and Gandini 2008; Choura *et al.* 1997). With an increasing awareness of sustainability and the emergence of bio-derived materials, there is also a similar need to consider more environmentally benign options for treating wood. Recently a promising wood modification using biopolymers based on glycolic and lactic acids and polybutylene succinate and polybutylene adipate esters was reported. Wood was treated with these polyesters in their oligomeric forms *via* a bulk impregnation and then polymerised *in-situ* within the wood to variously enhance wood properties such as dimensional stability (Noël *et al.* 2015a, 2015b, 2015c; Vitkeviciute, 2015). However, across these biopolyester treatments, differing degrees of impregnation and cell wall infiltration were observed, with corresponding variations in the *in-situ* polymerisation and wood properties (Figure 1). This was most contrasted by the polylactic acid (PLA) oligomer (OLA) and polybutylene succinate (PBS) oligomer (OBS) ester treatments.

Figure 1: Comparison of PLA and PBS oligomers efficiency for wood modification in relation to the cell wall modification

On impregnating oligomeric esters into wood, OLA-based treatments were revealed to be cell wall bulking, whereas OBS treatment remained lumen-filling only (Figure 1) (Noël *et al.* 2015a). This manifested in wood properties where OLA esters led to very good dimensional stabilisation (up to 75% ASE), but increased brittleness of the treated wood (unpublished results). In contrast, OBS esters (70% of polymers weight uptake in wood) decreased the wood hygroscopicity, but were found to provide only limited dimensional stabilisation (Noël *et al.* 2015a), most likely because of a highly hindered capillary conduction. In comparison to untreated wood exposed at high humidity, a lower equilibrium moisture content of OBS treated wood with identical resulting swelling can be explained by the partial OBS solubility. OBS oligomers are partially solubilized and transported to the cell wall. The swelling observed during high humidity exposure is thus due to water and oligomers diffusion and explains the decreased EMC. The OBS ester treatment did not influence the mechanical properties of the treated wood. Furthermore, as part of ASE evaluations, treated wood was observed to variously leach polyester materials when initially in contact with water on testing. While the leaching was considered relatively high for OLA treatments, the OBS oligomers appeared retained within the wood structure on water leaching, with only 20% of polymer loss (Noël *et al.* 2015a).

An aspect of OBS polyester treatment and testing was an unexpected improvement in ASE cyclic humidity testing performance after initial water soaking. Original, unleached OBS treated samples show no ASE*_{95%RH} as the cell walls were not impregnated (Figure 1). However, OBS treated samples initially exposed to water as part of leaching resistance testing were subsequently observed to have substantially improved properties as evidenced by high ASE*_{95%RH} values and no detrimental impact to mechanical performance (Noël *et al.*, 2015a). This unanticipated finding has prompted a further evaluation of biopolyester treatments using OBS oligomers together with attempts to optimise the processing of treated wood. This has included an evaluation of temperature and *in-situ* polymerisation times together with water treatment conditions to enhance OBS penetration into wood cell wall and wood property enhancement. Ultimately, the goal of this study is a range of tailored biopolyester treatments for the enhancement of wood stability and performance.

3. Experimental methods

3.1. Synthesis of the PBS oligomers (OBS)

Oligomeric polyesters were synthesised by their direct polymerisation under vacuum, using a four-necked flask fitted with a magnetic stirrer and reflux condenser linked to an

inline cold trap and vacuum pump. Thermometers were used to observe the polymerisation, condenser head, and heater temperatures.

Oligoesters (OBS) were synthesised by melt polymerisation of dimethyl succinate and 1,4-butanediol. This was achieved by adding a 25% stoichiometric excess of 1,4-butanediol in the presence of titanium (IV) butoxide as esterification catalyst. A mixture of dimethylester, 1,4-butanediol, and catalyst was poured into the flask under a nitrogen purge. The mixture was gradually heated to 180°C over 130 min under reduced pressure (150 mbar). At the end of the reaction, oligomers were poured into bottles, sealed and cooled. OBS esters solidify as a white block on cooling. The melt temperature of the resulting oligomeric OBS material was rheologically measured at *ca.* 75°C.

3.2. Wood treatment

Wood OBS oligomer treatments followed a published processing procedure (Noël *et al.* 2015a). Wood samples were immersed in liquid oligomers at 90°C as an initial impregnation step. Containers were then placed in a vacuum oven under reduced pressure (580 mmHg) for 40 min, then atmospheric pressure over 40 min. Impregnated samples were then wiped and set on aluminium foil in a ventilated oven under controlled temperature and duration (Table 1). Anhydrous sample weight was measured before impregnation, after impregnation and then after heat treatment. Weight uptake has been calculated according to Eqn. 1.

$$WU_{i/t} (\%) = \frac{w_{i/t} - w_0}{w_0} \times 100 \quad (1)$$

where w_i stands for the impregnated sample weight, w_t for the sample weight after complete treatment, and w_0 the oven dried sample weight before treatment.

3.3. Anti-swelling efficiency (ASE)

All treated samples (15 x 15 x 10 mm, T x R x L) were placed in 95% relative humidity (RH). Sample dimensions were measured before exposure in dry state (due to treatment process) and after weight stabilisation. Regular weight measurements were made in order to determine the equilibrium moisture content of samples with time and conditioning.

As some treatments show a strong bulking effect in the cell wall while others only penetrate wood lumens (Figure 1), the ASE calculation was based on the corrected swelling calculation of treated samples (S_t) as defined in Eqn. 2 (Thybring, 2013):

$$S_t^* (\%) = \frac{V_{95\%st} - V_t}{V_0} \times 100 \quad (2)$$

$$ASE^* (\%) = \frac{S_{nt} - S_t^*}{S_{nt}} \times 100 \quad (3)$$

where $V_{95\%st}$ stands for the treated sample volume after stabilisation at 95%RH, V_t for the treated sample volume before stabilisation at 95% RH, V_0 the oven dried sample volume before treatment and S_{nt} the reference untreated sample swelling:

$$S_{nt} (\%) = \frac{V_{95\%st} - V_{nt}}{V_{nt0}} \times 100 \quad (4)$$

where $V_{95\%st}$ stands for the reference untreated sample volume after stabilisation at 95%RH and V_{nt} for the oven dried reference untreated sample volume.

For treated samples, the reduced equilibrium moisture content EMC_{Rt} has been calculated as defined in Eqn. 5:

$$EMC_{Rt} (\%) = \frac{w_{95\%st} - w_t}{w_0} \times 100 \quad (5)$$

where $w_{95\%st}$ stands for the treated sample weight after stabilisation at 95%RH, w_t for the dry treated sample weight before stabilisation at 95%RH, and w_0 the oven dried sample weight before treatment.

The reduced EMC, or EMC_{Rt} , allows comparison of the different treatments by relating the water uptake to the dry wood weight, not taking in consideration the weight of polymer into wood structure which may differ between treatments.

Swelling and anti-swelling efficiency of samples soaked into liquid water were calculated as well according to formulae (2), (3) and (4) where “95%” can be replaced by “lw” standing for liquid water.

3.4. Leaching

The treatment resistance to water leaching was measured in terms of weight loss of polymeric material (WPL) resulting from the ASE test in liquid water. The samples were soaked in water at 23°C for 7 days. At the end of the test, the samples were air dried at 23°C / 56%RH for 24h and subsequently oven dried until constant weight. The WPL was calculated as defined in Eqn. 6:

$$WPL (\%) = \frac{w_{tl0} - w_t}{w_t - w_0} \times 100 \quad (6)$$

where w_{tl0} stands for the treated sample weight after leaching and oven drying, w_t for the treated sample weight (necessarily oven dried) and w_0 the oven dried sample weight before any treatment.

3.5. Dynamic Mechanical Analysis

The DMTA analysis has been carried out on a Triton TTDMA equipped with a humidity generator set up to allow a temperature ramp and the RH in the chamber for samples of dimensions 50 x 10 x 4 mm, L x RT x TR. The temperature changes were manually performed when the conditions in the chamber were stable. Once the temperature and RH were stable, the average of five values of the stabilised storage modulus, taken at 3 min intervals, was calculated with this average storage modulus value reported in Figure 5. Only thermal scans carried out at 1 Hz are reported in this paper.

Sample swelling was measured as the ratio between the sample volume after DMTA run and on further oven drying (at 103°C for 24h) and comparing with the initial dry sample volume immediately after the hot oligomer impregnation.

3.6. Durability assessment and natural weathering

1 A preliminary determination of the potential conferred durability has been carried out
2 according to a modified EN 113 standard, with the following variation: 11 week-
3 exposure to *Coriolus versicolor*, samples dimensions of 50 x 15 x 12.5 mm³. Virulence
4 controls showed a 14.5% weight loss, and did not reach the 25% threshold of the
5 standard. Samples treated with OBS (160°C / 2 days) and leached (according to the EN
6 84 standard, with following deviations: water boxes not placed in controlled conditions
7 of humidity and temperature, oven drying of samples after leaching instead of
8 stabilisation at 65%/20°C) have been tested, as well as untreated samples heated at
9 160°C for 2 days for evaluation of the thermal treatment influence.

10 Natural, outdoor weathering has been conducted in Biel (Switzerland) at 45° from the
11 ground with the sample wood grain direction exposed horizontally. The assessment was
12 conducted according to a modified EN 927-3 standard, with the following variation:
13 samples dimensions of 150 x 72 x 12 mm³ (L x R x T), no protection of the end-grain
14 and edges. Along the exposure, the following evaluations have been made: deformation,
15 cracking, colour homogeneity, mould attack, colour change.

18 **4. Results and discussion**

19 **4.1. *Relation of OBS treatment with water and wood***

22 Even if no direct correlation can be drawn between the behaviour of pure chemicals and
23 the behaviour of these chemicals in wood, the polyester was prepared in pure form so to
24 assess any responsiveness of OBS polyesters to exposure to varying humidity, and to a
25 near saturated environment (*ca.* 95% RH). This revealed that the sensitivity of OBS to
26 water sorption was relatively limited, and in accordance with literature (Phua *et al.*
27 2011; Tserki *et al.* 2006; Frollini *et al.* 2013). After 10 weeks exposure, weight
28 increases of less than 0.5% were observed with no distinctions between OBS polyesters
29 prepared at 140°C or 160°C. In contrast, polymerised OLA oligomers heated at 120°C
30 can absorb up to 28% moisture content at 95% RH (Vitkeviciute 2015). Furthermore,
31 water absorption profiles reveal OBS to rapidly achieve equilibration, whereas moisture
32 sorption by OLA polymer increases with time (Figure 2). It is also possible that the
33 polyester undergoes hydrolysis which may increase hydrophilicity, according to the
34 following process: the polymer degradation through ester bond hydrolysis leads to an
35 increased amount of carboxylic end groups, which are known to autocatalyse the ester
36 hydrolysis, and to an increase in acidity due to soluble oligomers leaching resulting in
37 accelerated degradation (Proikakis *et al.* 2006; Edlung and Albertsson 2003; Madhavan
38 Nampoothiri *et al.* 2010; Cho *et al.* 2001).

Figure 2: Moisture content of OLA and OBS oligomers, preliminary heated for 2 days at 140 °C, then exposed at 96%RH at room temperature [Vitkeviciute, 2015]

Figure 3: EMC_{Rt} of wood samples treated with OLA or OBS oligomers heated at 140°C for 6h or 3 days, then exposed to 96%RH at room temperature [Vitkeviciute, 2015]

An evaluation of moisture uptake at high humidity revealed wood samples treated with OLA show an increasing EMC_{Rt} over time, and this occurred at a greater rate when thermal treatment and *in-situ* polymerisation was short (6h, Figure 3). Similarly, samples treated with OBS also have greater moisture sorption when polymerised with a shorter thermal treatment. However, with these OBS samples the EMC_{Rt} profile

appeared stabilised (*ca.* 40%) after 6 weeks of exposure with the EMC_{Rt} comparable to the reference, untreated sample (Figure 3). This comparable EMC_{Rt} was consistent with the pure OBS polyester moisture uptake exhibited in Figure 2, but also suggests the impregnation treatment was insufficient to significantly decrease the EMC_{Rt} .

An evaluation of OBS treated samples which underwent the water soak leaching step revealed comparatively lower EMC_{Rt} profiles than unleached samples (95%RH at 23°C, Figure 4). Firstly, samples prepared with extended cure heating (160°C, 9 days) exhibited distinctly lower EMC_{Rt} profiles than moderately cured OBS samples (160°C, 2 days) (Figure 4). The influence of treatment duration and water leaching was shown with significantly lower EMC_{Rt} values after 240 days at 95%RH/23°C. Moreover, the trends in EMC_{Rt} values for leached OBS treated sample also manifested in the 95%RH/23°C ASE evaluations of these samples. In this case, the treated samples displayed greater dimensional stability ($ASE_{95\%RH}^*$ of *ca.* 40%) after the water leaching with up to 55% $ASE_{95\%RH}^*$ for the extended cure treatment (9 days at 160°C). Given these samples swell after leaching and drying, this suggests partial penetration of the OBS oligomers into wood cell walls, and may provide an insight to the observed ASE values.

Figure 4: EMC_{Rt} of OBS treated samples (160°C/2days and 9 days) and reference samples not heated, or heated (160°C/2 days and 9 days) along exposure time to 95%RH at 23°C (95%RH/23°C), or to water soaking (water)

To provide further understanding of the partial OBS oligomer penetration achieved on leaching, dynamic mechanical analysis (DMA) under fixed humidity (35%RH, 57%RH and 86%RH) was performed on treated and leached samples (Figure 5). The objective was to link the differing physico-mechanical properties of the wood with relative humidity and temperature using sample stiffness (storage modulus, E'). For the OBS treated sample at 35%RH, the E' decrease was relatively consistent from 20 to 40°C, decreasing by 0.4 GPa at 40°C. At 57%RH, the sample behaviour was relative similar,

also decreasing by 0.4 GPa. Moreover, the DMA heating induced swelling of the OBS sample by 5.6% and 7.4% at 35%RH and 57%RH, respectively (swelling measured at dry state after and before the test). At 85%RH, the E' loss of the OBS sample was higher (>0.8 GPa) and at a greater rate, resulting in 17.6% sample swelling. The analysis of volume gain indicates that with higher RH, each heating run allowed OBS material to penetrate into the cell wall contributing to greater swelling, and further confirmed by the observation that untreated samples do not swell. This initial relationship between the E' change and polymer cell wall penetration will require further study to better understand the mobility and interaction between OBS and wood components.

Figure 5: Relative storage modulus of samples impregnated (solid line), impregnated and leached (dotted line); at 35%RH, 57%RH and 85%RH along temperature increase from 20 to 50°C

For OBS impregnated and leached samples (where the polymer had been observed to penetrate cell walls), DMA revealed differing E' behaviours. At 35%RH, the E' loss of the leached sample was relatively similar to that for the impregnated sample and associated with swelling of 2.4%. At 57%RH, the E' curve was comparable to the impregnated sample, but with a greater decrease in E' value. However, sample swelling was only 1.7%. At 85%RH, the leached sample had a differing E' profile with only a moderate loss in E', similar to the untreated reference sample (not presented). The additional swelling of this sample was 3.7%, being significantly lower than the unleached sample. This suggests the heating of leached samples with increased humidity does not promote any significant additional cell wall penetration as observed with the impregnated-only samples.

4.2. Aging of OBS treated wood

OBS treated samples (160°C / 2 days) were exposed to outdoor weathering. After 12 months, the surface quality of treated samples was assessed as being better (no cracking and no mould attack) than the reference on which many wide and deep cracks were visible, as well as a darker coloration (Supplementary Material 1).

According to the preliminary durability assessment, OBS treated samples (160°C / 2 days) showed a weight loss of only 3.7% (17% for control samples), whereas untreated samples heated according to the same thermal treatment (160°C / 2 days) showed 12.2% weight loss (15.4% for control samples). Furthermore, there appeared a substantial fungicidal effect conferred by the OBS treatment which cannot be attributed to only the thermal treatment (Hakkou *et al.* 2006; Kamdem *et al.* 2002). Presently, further investigation is pending to determine if OBS treatment is fungicidal or if the decreased EMC conferred by this treatment contributes the improved durability.

4.3. Applications potential

Given the promising properties of the OBS treatment above and the previously reported results (Noël *et al.* 2015a), further samples were produced to determine OBS treatment efficiency (Table 1). A range of processing and cure temperatures (120°C and 140°C) were used, being intermediate temperatures relative to the previous sample treatments. This showed that treatment at differing temperature did not induce any swelling on impregnation (S_i), despite a high weight uptake (WU_i , *ca.* 65%) of most samples. Only for treatment of fresh, green wood (98% mc) was there no weight uptake nor swelling observed, likely a result of adsorbed water being replaced by the oligomer material which was associated with intense foaming from the sample during impregnation. The analysis of volume gain indicates that with higher RH, each heating run allowed OBS material to penetrate into the cell wall contributing to the observed greater sample swelling. In contrast, untreated samples do not swell under these conditions. The wet treatment followed by dry heating variously led to sample swelling (S_t) which was *ca.* 7% for high temperature drying samples (samples 3 and 5) and *ca.* 13% for wet step samples (samples 2, 7-16). Furthermore, wet heating for 30 min (samples 7, 9, 10) led to higher oligomer cell wall penetration than water leaching at room temperature (7 days, sample 2). A longer wet heating did not lead to higher swelling (samples 11-16). Comparing samples 9-16, it was observed that a longer heating step at higher temperature generally led to greater swelling (samples 10, 12, 14 and 16 in comparison to samples 9, 11, 13 and 15). A comparison of samples 7 and 9 shows that longer heat treatment at 103°C led to higher swelling, whereas the comparison of samples 7 and 10 shows that for a four-day heating step, a higher heating temperature did not lead to greater swelling. For samples 2 and 7-16 their wet treatment may have led to partial oligomer hydrolysis (Cho *et al.* 2001) promoting oligomer mobility into the cell wall together with leaching of oligomers from the wood.

Table 1: Treatment parameters evaluated

Ref.	EMC ^a [%]	Impregnation temperature [°C]	Wet step	Dry step
1	0	90	-	Oven heating, 103°C/12h
2	0	90	Water leaching, 23°C/7d	Oven heating, 103°C/2.5d
3	0	90	-	Oven heating, 140°C/12h
4	0	130	-	Oven heating, 103°C/12h
5	0	130	-	Oven heating, 140°C/12h
6	0	90	Wet heating, 100°C/100%RH/30min	-
7	0	90	Wet heating, 100°C/100%RH/30min	Oven heating, 103°C/4d
8	98 ^b	90	-	Oven heating, 103°C/4d
9	0	90	Wet heating, 100°C/100%RH/30min	Oven heating, 103°C/2.5d
10	0	90	Wet heating, 100°C/100%RH/30min	Oven heating, 120°C/4d
11	0	90	Wet heating, 100°C/100%RH/2h	Oven heating, 103°C/2.5d
12	0	90	Wet heating, 100°C/100%RH/2h	Oven heating, 120°C/4d
13	0	90	Wet heating, 100°C/100%RH/5h	Oven heating, 103°C/2.5d

14	0	90	Wet heating, 100°C/100%RH/5h	Oven heating, 120°C/4d
15	0	90	Wet heating, 100°C/100%RH/10h	Oven heating, 103°C/2.5d
16	0	90	Wet heating, 100°C/100%RH/10h	Oven heating, 120°C/4d

^aWood EMC before impregnation, ^bNon dried wood, freshly cut

Table 2: Treatments description and efficiency

Ref.	S _i [%]	WU _i [%]	S _t ^a [%]	WU _t ^a [%]	ASE [*] _{lw} ^b [%]	EMC _{Rtlw} ^b [%]	WLP [%]	S _{lw} ^c [%]	ASE [*] _{95%} ^d [%]	EMC _{Rt95%} ^d [%]
1	0.2 ± 0.4	66.6 ± 2.1	0.9 ± 0.3	64.6 ± 2.2	-1.4 ± 6.5	52.6 ± 0.8	-23.6 ± 0.4	5.6 ± 0.4	30.3 ± 5.8	31.4 ± 0.8
2	0.3 ± 0.1	65.3 ± 5.4	11.6 ± 0.7	49.6 ± 4.2	42.8 ± 4.4	56.9 ± 1.9	-5.2 ± 0.3	2.1 ± 0.3	55.2 ± 5.1	30.5 ± 0.5
3	-0.1 ± 0.3	63.8 ± 7.5	7.8 ± 0.3	55.2 ± 6.6	37.1 ± 3.2	53.8 ± 1.3	-7.3 ± 0.7	-2.1 ± 0.8	37.3 ± 6.3	28.0 ± 0.5
4	0.5 ± 0.4	62.6 ± 9.5	0.8 ± 0.1	60.8 ± 9.3	1.9 ± 11.9	55.6 ± 2.0	-21.2 ± 0.6	5.1 ± 0.7	33.2 ± 11.9	30.4 ± 1.0
5	0.8 ± 0.6	68.2 ± 5.5	6.7 ± 1.1	63.0 ± 5.1	29.3 ± 9.7	55.6 ± 3.1	-11.7 ± 1.0	0.5 ± 1.5	40.1 ± 9.8	30.5 ± 1.3
6	0.5 ± 0.2	64.2 ± 5.5	- ^e	- ^e	- ^e	- ^e	- ^e	- ^e	18.3 ± 7.6	31.8 ± 1.7
7	0.7 ± 0.4	65.2 ± 7.4	14.9 ± 1.0	51.9 ± 7.2	53.8 ± 3.8	61.0 ± 0.6	-16.4 ± 1.0	-1.9 ± 0.8	47.8 ± 7.2	30.5 ± 1.0
8	-2.4 ± 1.4	-1.8 ± 0.9	12.0 ± 1.2	57.4 ± 5.5	56.9 ± 4.3	48.0 ± 3.4	-19.5 ± 0.9	-0.8 ± 0.8	55.1 ± 4.9	29.4 ± 2.1
9	0.7 ± 0.4	74.4 ± 3.8	8.8 ± 0.4	70.5 ± 3.2	36.8 ± 6.5	53.7 ± 1.9	-18.0 ± 0.5	-3.8 ± 0.8	64.0 ± 5.8	24.5 ± 0.6
10	0.9 ± 0.4	75.3 ± 7.4	12.3 ± 0.8	69.8 ± 7.4	43.6 ± 4.7	50.4 ± 1.4	-14.1 ± 0.5	-4.1 ± 0.9	70.8 ± 3.5	23.9 ± 1.0
11	0.5 ± 0.1	67.2 ± 7.5	14.5 ± 1.3	63.6 ± 7.2	50.6 ± 6.7	55.8 ± 4.1	-17.0 ± 0.9	-1.1 ± 0.8	52.8 ± 8.3	25.6 ± 0.9
12	0.5 ± 0.2	67.4 ± 7.2	16.0 ± 0.6	61.6 ± 8.2	61.9 ± 2.7	57.4 ± 2.2	-14.0 ± 0.3	-1.4 ± 0.6	68.7 ± 1.4	25.1 ± 1.0
13	0.3 ± 0.2	60.8 ± 5.8	15.0 ± 1.1	58.1 ± 7.3	51.1 ± 8.4	53.5 ± 1.7	-15.2 ± 0.7	-0.5 ± 0.6	54.7 ± 2.3	25.4 ± 0.5
14	0.3 ± 0.2	65.0 ± 3.3	17.1 ± 0.4	60.1 ± 4.0	62.9 ± 3.3	53.9 ± 1.4	-12.3 ± 0.8	-2.6 ± 0.2	71.1 ± 1.6	25.0 ± 0.4
15	0.6 ± 0.4	69.0 ± 4.1	13.6 ± 2.1	55.8 ± 8.0	42.1 ± 10.6	59.8 ± 3.0	-16.1 ± 0.8	0.1 ± 1.2	46.0 ± 7.1	25.1 ± 0.3
16	0.1 ± 0.2	68.6 ± 4.0	17.1 ± 0.7	59.0 ± 5.9	60.8 ± 2.4	59.7 ± 1.0	-12.5 ± 0.7	-1.8 ± 0.8	66.5 ± 1.6	25.1 ± 0.3

^aTreatments are defined in Table 1. They consist in the wet and dry step. ^bASE^{*} and EMC_{Rt} in liquid water. ^cSwelling measured after the water leaching and oven drying. ^dASE^{*} and EMC_{Rt} at 95%RH. ^eThis data could not be calculated because the ASE_{lw} step directly followed the wet step. An intermediate drying would have been necessary for the calculation.

To further characterise the treatment effectiveness, ASE values were determined in both liquid water (23°C/7d, measured as ASE_{lw}), and then after oven drying (103°C) subjection to 95%RH/23°C conditioning (ASE_{95%}, Table 2). For samples immersed in water, the EMC_{Rt} values were found to be *ca.* 55%, but the ASE^{*} were highly dependent on the treatment process. Samples 7, 8, 12, 14 and 16 attained the highest ASE_{lw} values (*ca.* 55-60%) with the high initial sample EMC and the wet heating followed by long heating at high temperature, suggestive of efficient processing compared to water soaking prior to heating (sample 2, 43% ASE). With slightly lower swelling (S_t), samples 9 and 10 led to lower ASE_{lw}. High temperature drying with no wet step (140°C, samples 3 and 5) lead to ASE_{lw} values of *ca.* 30%. This result suggests a high *impregnation* temperature does not improve the stability properties which was also observed with samples 1 and 4 which had no ASE and used the lower (103°C) heating temperature.

Typically, conditioning in high humidity revealed most samples to have high EMC_{Rt} values (*ca.* 25-30%) with samples distinguished by differing ASE*_{95%} values. Samples 2 and 8 have the similar ASE*_{95%} (55%) demonstrating that either water leaching at room temperature or oligomer impregnation of wet wood led to similar treatment efficiency. High temperature heating conferred an ASE*_{95%} value of *ca.* 40%, showing that the temperature was not the most significant parameter in this treatment. Samples 1 and 4 which do not have a wet step and use the lower temperature heating step gave ASE*_{95%} values of 30%. In the case of sample 6 which had the lowest ASE*_{95%} value of 18% suggests the wet step needs to be followed by a dry heating step to confer dimensional stability. Samples 12, 14 and 16 which have the greatest ASE*_{95%}, confirm this observation.

The influence of temperature and humidity on the treatment efficiency was confirmed with these results. A high wood EMC before impregnation or a wet heating step after impregnation led to better performance than a room temperature water soaking before dry heating. Increasing the dry heating temperature also led to better performance than a higher impregnation temperature. It is hypothesised that the wood cell wall swelling induced either by the high wood EMC before impregnation, or by a wet heating step, contributed to the partial dissolution of OBS oligomers during this process and allowed higher oligomer diffusion into the wood structure. Higher temperatures are likely to decrease OBS oligomer viscosity, also contributing to the partial product diffusion into the cell wall, but to a lesser extent than where wood is swollen by water or humidity. Moreover, contact of wood and polymer at high temperature must be sufficient to observe this effect and may explain why an 80 min impregnation step gave lower treated wood performance compared to 12h, 2.5d or 4d heating steps.

5. Conclusions

A comprehensive evaluation of OBS biopolyester impregnation followed by moisture exposure and a second heating step has confirmed this treatment process confers dimensional stability to the treated wood. Results indicate the OBS oligomers can be impregnated in wood over a range of temperatures (90-130°C). While this treatment alone is predominantly lumen filling, a subsequent water soak step then drying step can enhance wood dimensional stability in both liquid water and high humidity. This was likely through partially hydrolyzed OBS oligomer diffusion to the cell wall contributing the dimensional stability and performance improvements in weathering and durability evaluations.

Attempts to define the water exposure and dry heating steps to optimise OBS oligomer treatment revealed impregnation can be undertaken over a range of temperatures from 90 to 130°C. Samples can then be processed in a wet state either by water soaking or wet heat (100°C) to promote oligomer hydrolysis and migration into wood cell walls. The temperature of the final dry heating step contributes to treatment efficacy where a higher temperature was associated with greater dimensional stability. Further understanding of the degree of hydrolysis and polymerisation rate required within these treatment steps will further aid optimisation and enhancement of this promising wood treatment.

6. Acknowledgements

The authors would like to acknowledge Christian Brönnimann, Aurèle Bourquin and Charlotte Grosse for laboratory work, together with Patrick Kaiser and María-Inés

Placencia Peña. Thanks is also extended to the COST Organisation, through COST Action FP1303 for financial support to conduct a short term scientific mission (Grant letter STSM-FP1303-100515-060044) at the BioComposites Centre laboratories in Bangor (Wales) where TTDMA work was undertaken. This paper is part of a special issue of the 8th European Conference on Wood Modification.

7. References

Belgacem, N. M., Gandini, A. 2008. Chemical modification of wood. In: Monomers, polymers and composites from renewable resources, Elsevier, Oxford, UK, p.20.

Chang, H. T., Chang, S. T. 2002. Moisture excluding efficiency and dimensional stability of wood improved by acetylation. *Bioresource Technol*, **85**, 201-204.

Cho, K., Lee, J., Kwon, K. 2001. Hydrolytic degradation behavior of poly(butylene succinate)s with different crystalline morphologies. *J Appl Polym Sci*, **79**, 1025-1033.

Choura, M., Belgacem, N. M. and Gandini, A. 1997. The acid-catalyzed polycondensation of furfuryl alcohol: old puzzles unraveled. *Macromol Symp*, **122 (1)**, 263-268.

Edlund, U., Albertsson, A.-C. 2003. Polyesters based on diacid monomers. *Adv Drug Deliver Rev*, **55**, 585-609.

EN 113:1997 standard. Wood preservatives. Test method for determining the protective effectiveness against wood destroying basidiomycetes. Determination of the toxic values.

Frollini, E., Bartolucci, N., Sisti, L., Celli, A. 2013. Poly(butylene succinate) reinforced with different lignocellulosic fibers. *Ind Crop Prod*, **45**, 160-169.

Hakkou, M., Pétrissans, M., Gérardin, P., Zoulalian, A. 2006. Investigations of the reasons for fungal durability of heat-treated beech wood. *Polym Degrad Stabil*, **91**, 393-397.

Hill, C.A.S. 2006. Wood modification – chemical, thermal and other processes. Chichester: John Wiley & Sons.

Ibach, R. E., Ellis, W. D. 2005. Lumen modifications. In: Handbook of wood chemistry and wood composites. Boca Raton, FL: CRC press. p.15.

Kamdern, D.-P., Pizzi, A., Jermannaud, A. 2002. Durability of heat-treated wood. *Holz Roh Werkst*, **60 (1)**, 1-6.

Lande, S., Westin, M. and Schneider, M. H. 2004. Eco-efficient wood protection: furfurylated wood as alternative to traditional wood preservation. *MEQ*, **15(5)**, 529-540.

Madhavan Nampoothiri, K., Nimisha Rajendran Nair, Rojan Pappy John, 2010. An overview of the recent developments in polylactide (PLA) research. *Bioresource Technol*, **101**, 8493-8501.

Noël, M., Grigsby, W., Vitkeviciute, I., Volkmer, T. 2015a. Modifying wood with bio-polyesters: analysis and performance. *J I Wood Sci*, **6(1)**, 14-20.

Noël, M., Grigsby, W., Volkmer, T. 2015b. Evaluating the extent of bio-polyester polymerization in solid wood by thermogravimetric analysis. *J Wood Chem Technol*, **35**, 325-336.

Noël, M., Grigsby, W., Volkmer, T. 2015c. Investigating the viscoelastic properties and mechanical performance of wood modified by biopolyester treatments. *JRM*, **2(4)**, 291-305.

Phua, Y. J., Chow, W. S., Mohd Ishak, Z. A. 2011. The hydrolytic effect of moisture and hygrothermal aging on poly(butylene succinate)/organo-montmorillonite nanocomposites. *Polym Degrad Stabil*, **96**, 1194-1203.

prEN 927-3:2010. Paints and varnishes. Coating materials and coating systems for exterior wood – Part 3: Natural weathering test.

Proikakis, C. S., Mamouzelos, N. J., Tarantili, P. A., Andreopoulos, A. G. 2006. Swelling and hydrolytic degradation of poly(D,L-lactic acid) in aqueous solutions. *Polym Degrad Stabil*, **91**, 614-619.

Rowell, R. M. 2005. Chemical modification of wood. In: Handbook of wood chemistry and wood composites. Boca Raton, FL: Taylor and Francis. p.14.

Thybring, E. E. 2013. The decay resistance of modified wood influenced by moisture exclusion and swelling reduction. *Int Biodeter Biodegr*, **82**, 87-95.

Tserki, V., Matzinos, P., Panayiotou, C. 2006. Novel biodegradable composites based on treated lignocellulosic waste flour as filler Part II. Development of biodegradable composites using treated and compatibilized waster flour. *Compos Part A-Appl S*, **37**, 1231-1238.

Vitkeviciute, I. 2015. Sorption of water vapour by bio-(co)polyesters modified beech wood », MSc Thesis Wood Technology, Products and Processes, Berne University of Applied Sciences, Biel, Switzerland.

Xie, Y., Krause, A., Mai, C., Militz, H., Richter, K., Urban, K., Evans, P. D. 2005. Weathering of wood modified with the N-methylol compound 1, 3-dimethylol-4, 5-dihydroxyethyleneurea. *Polym Degrad Stabil*, **89**, 189-199.

8. Figure captions

Figure 1: Comparison of PLA and PBS oligomers efficiency for wood modification in relation to the cell wall modification

Figure 2: Moisture content of OLA and OBS oligomers, preliminary heated for 2 days at 140 °C, then exposed at 96%RH at room temperature [Vitkeviciute, 2015]

Figure 3: EMC_{Rt} of wood samples treated with OLA or OBS oligomers heated at 140°C for 6h or 3 days, then exposed to 96%RH at room temperature [Vitkeviciute, 2015]

Figure 4: EMC_{Rt} of OBS treated samples (160°C/2days and 9 days) and reference samples not heated, or heated (160°C/2 days and 9 days) along exposure time to 95%RH at 23°C (—95%RH/23°C), or to water soaking (—water)

Figure 5: Relative storage modulus of samples impregnated (solid line), impregnated and leached (dotted line); at 35%RH, 57%RH and 85%RH along temperature increase from 20 to 50°C

Figure S1: Wood samples exposed for one year outdoors. (A) OBS-treated samples (160°C / 2 days) (B) untreated reference (pictures have been slightly and equivalently lightened to make the cracks more visible)

9. Table captions

Table 1: Treatment parameters evaluated

Table 2: Treatments description and efficiency

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Supplementary materials list

Figure S1 is an illustration of the weathering of untreated and treated wood outdoors, where many deep cracks and a dark grey colour are observable on the untreated wood, whereas the OBS-treated wood remains brown and shows an undegraded surface after one year of exposure.

Caption of Figure S1:

Figure S1: Wood samples exposed for one year outdoors. (A) OBS-treated samples (160°C / 2 days) (B) untreated reference (pictures have been slightly and equivalently lightened to make the cracks more visible)