

**Assessment of the use of dynamic mechanical analysis to investigate initial onset of brown rot decay of Scots pine (*Pinus sylvestris* L.)**

Ormondroyd, Graham; Alfredsen, Gry; Raghavalu Thirumalai, Durai; Curling, Simon; Stefanowski, Bronia; Spear, Morwenna; Gobakken, Lone Ross

International Biodeterioration and Biodegradation

DOI:

[10.1016/j.ibiod.2017.02.002](https://doi.org/10.1016/j.ibiod.2017.02.002)

Published: 01/05/2017

Peer reviewed version

[Cyswllt i'r cyhoeddiad / Link to publication](#)*Dyfyniad o'r fersiwn a gyhoeddwyd / Citation for published version (APA):*

Ormondroyd, G., Alfredsen, G., Raghavalu Thirumalai, D., Curling, S., Stefanowski, B., Spear, M., & Gobakken, L. R. (2017). Assessment of the use of dynamic mechanical analysis to investigate initial onset of brown rot decay of Scots pine (*Pinus sylvestris* L.). *International Biodeterioration and Biodegradation*, 120, 1-5. <https://doi.org/10.1016/j.ibiod.2017.02.002>

Hawliau Cyffredinol / General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal ?

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

1 Assessment of the use of dynamic mechanical analysis to investigate 2 initial onset of brown rot decay of Scots pine (*Pinus sylvestris* L.)

3
4 Ormondroyd, G.A.^{1,3,*} Alfredsen, G.² Durai Prabhakaran, R.T.¹ Curling, S.F.¹ Stefanowski,
5 B.K.¹ Spear M.J.¹ Gobakken, L.R.²

6 ¹ The BioComposites Centre, Bangor University, Gwynedd, LL57 2UW UK

7 ² Norwegian Institute of Bioeconomy Research, Box 115, NO-1431 Ås, Norway

8 ³ Department of Architecture and Civil Engineering, University of Bath, Bath, UK

9 * Corresponding author. Tel. +44 (0)1248 383898 E-mail address:

10 g.ormondroyd@bangor.ac.uk (G.A. Ormondroyd)

11 12 Abstract

13 Microbiological degradation of wood by decay fungi can cause a rapid change in the
14 structural properties of timber which can result in both strength and mass loss.
15 Traditional techniques for the evaluation of decay (e.g. mass loss) lack the sensitivity to
16 evaluate the effects of the very first stages of the decay process. This paper describes the
17 effects of initial brown rot decay, defined by the amount of *Poria placenta* genomic DNA
18 (gDNA) present in the samples, on the dynamic mechanical properties of the timber. It
19 was found that there is a correlation between the mean storage modulus of the timber
20 and the amount of *P. placenta* gDNA present, and therefore the level of decay. This
21 shows that using dynamic mechanical analysis is a viable technique that can be used to
22 study initial decay processes.

23
24 **Keywords:** decay, *Poria placenta*, viscoelastic behaviour, dynamic mechanical analysis
25 (DMA),

26 27 1. Introduction

28 Microbiological degradation of wood by fungi can cause a rapid change in the structural
29 properties of timber (Jellison et al., 2013), however traditional techniques for the
30 evaluation of the decay (e.g. mass loss) lack the sensitivity to evaluate the effects of
31 decay in the very first stages of the decay process.

32 The mechanism for the decay of timber via brown rot is through oxidative and
33 enzymatic reactions (Goodell et al., 1997; Arantes et al., 2012; Alfredsen et al., 2015,
34 Zelinka, 2016). The fungus initiates the production of hydroxyl radicals by secreting
35 hydrogen peroxide and reductants in to the cell wall. The reductants reduce the ferric
36 iron (Fe³⁺) to ferrous iron (Fe²⁺) (Goodell et al., 1997; 2006), which then reacts with the
37 hydrogen peroxide to form hydroxyl radicals in the Fenton reaction. The hydroxyl
38 radicals depolymerize hemicelluloses and cellulose, modify lignin and generate
39 sufficient rearrangements in the cell wall to allow the hydrolysing enzymes to diffuse in
40 to the wall and degrade the polysaccharides (Goodell et al., 1997; Baldrian and
41 Valaskova, 2008; Arantes et al., 2012). Ray et al. (2010) terms the above mechanism the
42 Early Stage Decay Mechanism (ESDM) and suggest that it can act both rapidly and
43 extensively. This mechanism has also been referred to as chelator-mediated Fenton

44 (CMF) reaction (Arantes and Goodell 2014). Green et al. (1997) and Cowling (1961)
45 both noted that whilst the reduction in the degree of polymerization is rapid there is low
46 mass loss at this stage of decay. The study of early onset decay has, in recent years, been
47 furthered by the use of molecular techniques. gDNA quantification has shown to be
48 more sensitive than ergosterol and kition assays for estimation of fungal biomass in
49 early stages of decay both in sterile laboratory samples (Eikenes et al. 2005) and for
50 field samples (Pilgård et al. 2011). Hietala et al. (2014) found that the suppressive effect
51 of suboptimal temperature on wood decay caused by *P. placenta* appeared more
52 pronounced in Scots pine heart wood than in sapwood. At 30°C heartwood showed no
53 mass loss, poor substrate colonization (gDNA quantification) and marker gene
54 transcript level profiles indicating a starvation situation.

55 Alfredsen et al. (2015) reviewed the role of quantitative gDNA and gene expression
56 studies in the understanding of the mode of action of brown rot decay on modified
57 wood, charting the method development and recent studies. Based on gene profiles the
58 studies provide indications of a possible shift toward increased expression, or at least no
59 down regulation, of genes related to oxidative metabolism and no reduction, or
60 concomitant reduction, of genes related to the enzymatic breakdown of polysaccharides
61 in modified wood compared to untreated control. Using gene expression Ringman et al.
62 (2014) showed that *P. placenta* was present in acetylated, DMDHEU-treated and
63 thermally modified wood after 2 days while at 6 days, the gene expression levels were
64 significantly different from zero. Alfredsen et al. (2016) found *P. placenta* gDNA in
65 acetylated samples with high treatment level (22% acetyl content) after four weeks
66 while initial mass loss was not detected until 20 weeks. It is interesting to note that the
67 time to mass loss of the acetylated timber was in agreement with other researchers (Hill
68 et al., 2006). However, fungus was present in the timber much earlier in the test, which
69 suggests a good efficiency of acetylation in the prevention of decay.

70 Compositional data and structural properties of wood have also been used in
71 investigating the early stages of brown rot decay. Monrroy et al. (2011) assessed the
72 change in the degree of polymerization of the cellulose (of *Pinus radiata*), the crystalline
73 structure of the cellulose and the hemicellulose content of the wood over a decay period
74 of 8 weeks (using 20mm x 25mm x 5mm chips). Different species of brown rot were
75 assessed with *Gloeophyllum trabeum* showing the highest rate of cellulose degree of
76 polymerisation reduction and *Laetiporus sulphureus* showing a comparable loss in
77 cellulose crystallinity. Curling et al. (2002) examined the effect on the hemicellulose
78 content and the mechanical properties of southern yellow pine exposed to brown rot
79 fungi. Their data showed that during initial decay, where there was negligible weight
80 loss (up to 20 days exposure), there were significant changes in hemicellulose content
81 associated with up to a 20% loss in modulus of elasticity, 40% loss in modulus of
82 rupture (4 point bending strength) and 80% loss in work to maximum load. This
83 indicates that physical properties may be a more appropriate method of studying early
84 stage decay than simple mass loss. Their method used static mechanical tests to derive
85 the data, although there is another physical characterisation method, Dynamic
86 Mechanical Analysis (DMA), which has become a well-established technique for
87 dynamically measuring the viscoelastic behaviour of polymers and polymer composites.
88 The earliest examples of DMA studies on wood were in the 1960s using torsional
89 pendulum apparatus (Norimoto and Yamada, 1966; Becker and Noack, 1968). DMA is
90 often used to measure the response of a material to changes at the molecular or
91 microstructural level (often but not always brought on by a change in temperature). In

92 their paper, Birkinshaw et al. (1986) assess the response of 10 timber species to
93 dynamic flexing whilst being subjected to a temperature gradient raising from 10 °C to
94 100 °C at 10 °C h⁻¹. The species were selected for their variety in densities and in
95 microstructure. It was noted that whilst the absolute values had a large variation the
96 general shape of the shear storage modulus curve and the loss modulus (tan δ) were
97 similar. Much research has been undertaken to determine the response to changes in
98 both temperature and humidity; the effect of the humidity and moisture content of the
99 wood on the glass transition temperature (T_g) and other relaxations of the lignin and
100 hemicelluloses of wood; and the effect on the mechanical properties of the timber (Hillis
101 and Rossa, 1978, 1985; Kelley et al., 1987; Salmén and Olsson, 1998; Olsson and Salmén
102 2004).

103 An important factor in the use of DMA is the determination of the Linear Viscoelastic
104 Response region (LVR), and experiments should be conducted within this region. Within
105 this region the strain is directly proportional to the stress and therefore the polymer
106 packing is not altered by the stress applied; however, once the response becomes non-
107 linear the polymer packing is being significantly and irreversibly altered. Sun et al.
108 (2007) used DMA to assess the dynamic response of timber at low moisture content
109 (<1%); they noted that the LVR was very low, between 0.03% and 0.16% strain
110 although values were greater when bending perpendicular to the grain.

111 McCarthy et al. (1991) studied the fungal degradation of wood via DMA. Small samples
112 were exposed to the brown rot fungus *Coniophora puteana* over a six week period on a
113 weekly basis in accordance with ASTM D2017 and DIN 50 008. The response to dynamic
114 loading was measured between -100 °C and 250 °C at a heating rate of 5 °C min⁻¹. The
115 researchers showed that the shear modulus fell with increased amounts of decay at all
116 temperatures. It was noticed that whilst the absolute values for the modulus changed
117 with the increase in decay, tan δ and the shape of the shear modulus curve did not
118 change significantly. It should be noted that this is in agreement with the earlier work of
119 Birkinshaw et al. (1986), in that there are changes in the absolute values but not the
120 location of the tan δ peak. Whilst we understand that the oxidative reaction
121 depolymerizes the wood holocelluloses prior to the components being utilized by the
122 fungi (which does not lead to a mass loss), the implication of this research is that the
123 ultimate degradation of the polymers responsible for the stiffness of the wood is
124 relatively uniform in rate.

125 The investigations undertaken to date have focused on the assessment of wood's ability
126 to respond to a dynamic temperature range and the effects of altering the molecular and
127 microstructure of the wood. The objective of this study was however, to determine the
128 potential of DMA, under isothermal conditions, as a method for the assessment and
129 quantification of initial onset brown rot decay.

130

131 **2. Materials and methods**

132 Scots pine (*Pinus sylvestris* L.) from South Norway was supplied by Norwegian Institute
133 of Bioeconomy Research Norway. The pine was straight grained and had an average
134 growth ring distribution of 10 rings/cm. The Scots pine was then machined to 2 mm x 2
135 mm strips and samples were selected to achieve 1 single latewood band through the
136 centre of the strip. All samples were conditioned to 65% RH at 20 °C before testing.

137 *2.1. Fungal exposure*

138 Fungal cultures of *Poria placenta* ((Fries) Cooke sensu J. Eriksson) (FPRL 280)
139 (originally from the European recognized holding lab as defined in EN 113) were grown
140 on 90 mm Petri dishes containing 4% malt agar (Malt extract powder 40 g; Agar 20 g;
141 Deionised water 1 litre). *P.placenta* (FPRL 280) is a fungal isolate stipulated by a number
142 of European testing standards for example EN113 (CEN 2004). Once the fungal culture
143 had grown to cover the entire surface of the plate the cultures were ready for samples.
144 Wood samples (2 mm x 2 mm x 80 mm) were cleaned by immersing them in ethanol for
145 1 minute. The samples were then dried and vented aseptically using a laminar flow
146 bench. Once dry, the samples were aseptically placed onto the pre-prepared fungal
147 cultures as follows: two samples were placed in direct contact with the agar/fungus to
148 act as supports, with three further samples placed perpendicular and on top of the
149 supports. This was intended to prevent water logging which may have prevented decay.
150 The cultures were then incubated at 22 °C ±2 at 70% RH ±3 with replicate samples
151 (n=6) removed (aseptically) from incubation after 4, 8, 11 and 17 days. Upon removal
152 from test the wood samples were dried for 12 hrs at 50 °C in order to stop fungal growth
153 without degrading any DNA. Dried samples were stored in sterile tubes before
154 subsequent DNA isolation and testing.

155 2.2. Assessment of the decay

156 As weight loss is not an accurate measure of the early onset of brown rot decay, gDNA is
157 used as a measure of fungal activity and the storage and loss modulus at different early
158 decay stages are compared against gDNA quantification.

159

160 2.2.1. Genomic DNA extraction

161 From each decay duration a 0.4 g sample of wood was subsampled from the total
162 population (n=3). This sample was then cut to small pieces and then manually ground
163 with a pestle and mortar under liquid nitrogen. The samples were then dismembrated for
164 2 x 2 minutes at full speed (with an intermediate liquid nitrogen freezing step) to ensure
165 a consistent powder was achieved (Retsch 300 mill, Retsch GmbH, Haan, Germany).
166 Aliquots of 20 mg were prepared from the powdered material and total gDNA was
167 extracted using DNeasy Plant Kit (Qiagen, Hilden, Germany) which works well for
168 extracting fungal DNA. The manufacturer's protocols were followed. Extractability of
169 gDNA from environmental samples, such as wood, can vary from sample to sample.
170 Hence, to normalise for this potential variation, 0.5 ng of reference DNA pGEM plasmid
171 (pGEM-3Z Vector, Promega, Madison, Wisconsin, USA) was added to each sample at the
172 start of the gDNA isolation (Coyne et al. 2005). The extracted gDNA was eluted in 50 µl
173 of buffer AE and stored in a fridge overnight.

174 2.2.2. qPCR analysis

175 gDNA from *P. placenta* was quantified using quantitative polymerase chain reaction
176 (qPCR) with the ViiA 7 (Applied BioSystems, Foster City, California, USA). A 10 µl PCR
177 reaction using TaqMan@SYBR@green mix (Applied Biosystems, Foster City, CA, USA)
178 and 300 nM concentration for the forward primer ACGCCCTGCTCTTCCATTC and
179 reverse primer AAACAGCATCCCCGTTAGA targeting the *P. placenta* internal
180 transcribed spacer (ITS) gene (GenBank accession EF524035). A 2 µl template of DNA
181 solution was used both for experimental samples and standard curve. Standard PCR
182 cycling parameters, according to ViiA 7 (Applied BioSystems, Foster City, California,
183 USA), were applied.

184 Duplicate runs were performed for undiluted, 10- and 100-fold dilutions of all samples.
185 Samples for standard curve was included in each plate.

186 The internal standard pGEM was quantified in a 10 µl PCR reaction with a 300 nM
187 concentration of the forward primer CCCAGTCACGACGTTGTAAAACG, reverse primer
188 TGTGTGGAATTGTGAGC GGA and the FAM-labelled TaqMan® probe (Applied
189 Biosystems, Foster City, CA, USA) CACTATAGAATACTCAAGCTTGCATGCCTGCA (Coyne et
190 al. 2005) and qPCR was performed on the samples (ViiA 7, Applied BioSystems, Forster
191 City, California, USA).

192 After amplification the data was analysed and plotted using the ViiA 7 software v1.2.4
193 (Applied BioSystems, Forster City, California, USA). The extent of amplification was
194 calculated as the mean of 2 replicates from each sample. The yield of *P. placenta* gDNA
195 was adjusted in relation to the recovery rate of the pGEM reference DNA (Hietala et al.
196 2014). The same trend was found for undiluted, 10-fold and 100-fold dilutions, but the
197 100-fold gave a slightly better yield and is presented in the results chapter.

198

199 **2.3. Dynamic Mechanical Analysis**

200 Dynamic Mechanical Analysis (DMA) was performed on a Triton Technology DMA, using
201 a three point bending mode. The samples were simply supported with a span length of
202 35mm. A preload force of 0.6 N was applied to ensure that the sample remained under
203 loading throughout the oscillation of the applied cyclic force. The amplitude of
204 displacement was 0.05 mm at a frequency of 1 Hz. This displacement equated to a strain
205 of 0.048 to 0.053%, which is well within the LVR for pine as reported by Sun et al.
206 (2007). The experiment was conducted under isothermal conditions at nominally 25 °C.
207 During the experiments, the temperature showed an increase of no more than 1.0 °C.
208 The isotherm was maintained for 90 minutes.

209 Samples of 43 mm (±2 mm) length were cut from the samples exposed to the test fungi
210 as described above. The approximate dimension of cross section was 2 mm x 2 mm,
211 however each was measured using a digital calliper (2 d.p.) after drying prior to loading
212 to the DMA, to ensure precise dimensions were used in the calculation of moduli. The
213 sample was aligned in the machine such that the tangential orientation was parallel to
214 the axis of the applied load. The samples were prepared by drying overnight at 50 °C,
215 and their weight recorded prior to test and at the end of the DMA run. The moisture
216 uptake by the samples over the test duration was noted.

217 The TTDMA recorded Storage Modulus (E') and Loss Modulus (E'') at intervals of 11 s.
218 The tan δ value was also calculated as the ratio of Loss Modulus to Storage Modulus. To
219 quantify the mechanical changes, complex modulus (E*) was chosen as the analysis
220 criterion, where $E^* = E' + n E''$ and n was assumed to be unity.

221

222 **3. Results and Discussion**

223 *3.1. Assessment of early onset decay*

224 qPCR analysis was used to quantify the presence of *P. placenta* gDNA within the wood
225 samples. Figure 1 shows the presence of the *P. placenta* gDNA in the decayed samples,
226 and an increasing trend in the amount of gDNA as the exposure time increases, **this is in**
227 **agreement with the recent work of Ringman et al. (2014) and Alfredsen et al. (2015,**
228 **2016).**

229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271

Figure 1: Quantity of fungal gDNA isolated (calculated from 100 factor dilution) from wood sample exposed to *P. placenta* for varying time periods

3.2. Dynamic Mechanical Analysis

The Dynamic Mechanical Analysis of decay timber has been the subject a very limited studies with only the studies of Birkenshaw et al. (1986) and Monrroy et al. (2011) being prominent within the literature. Further, neither of the two studies deal with initial on-set decay and therefore are not comparable to this study.

A typical DMA output for this isothermal experiment is shown in Figure 2. The control samples, and the majority of decayed samples showed similar behaviour over the 90 minute experimental period. The initial value of E' was low, and E' increased relatively rapidly over the first few minutes of the experiment. Thereafter the rate of increase slowed and the value tended towards a plateau value, however continuous small upward change was seen throughout the 90 minute period. The increase in E' was accompanied by a decrease in loss modulus (E''), and a corresponding decrease in the $\tan \delta$ value. This behaviour has not been previously reported, but isothermal DMA studies of wood are relatively unexplored. It is suggested that the increase in observed stiffness may be related to changes in dimensions which accompany alteration of moisture content, or to testing outside the linear viscoelastic response region (LVR).

In this study, the moisture content was observed to increase by a small amount during the test period. Values of 1.3 to 3.2% M.C. were determined at the end of the DMA run. This corresponds with gain of moisture from the atmosphere, and would conventionally be related to a decrease in stiffness (Wilson 1932), rather than the increase observed here. However, moisture content change is likely also to cause small dimensional changes in the cross section of the sample. The change in observed stiffness over time, and any correlation with dimensional change, or effects of moisture sorption within the sample during this period is likely to be complex, and worthy of additional study beyond this present work.

Figure 2. Storage Modulus, Loss Modulus and $\tan \delta$ throughout the isothermal DMA experiment, control sample 3.

Due to the evolution of E' and E'' values throughout the test period, data from different time intervals was compared. The average of the initial five data points was calculated as the start value; in addition the value at 60 s was used, and values at 1000 s, and at 3600

272 s within the plateau region were used. It was found that similar trends occurred in the
273 storage modulus and complex modulus data from the start, middle and plateau stages of
274 the experiment, whereas greater variation was seen in the viscoelastic components (loss
275 modulus and $\tan \delta$). This may indicate that further experimentation using temperature
276 scan experiments would provide additional information about changes within the
277 amorphous cellulose and hemicellulose regions of the wood cell wall, relating to
278 viscoelastic response of the material. This will be the subject of further study, however
279 within this paper the elastic component (E') will be considered.

280 The storage modulus and complex modulus showed similar trends for the samples
281 tested (Figure 3). The values for unexposed control samples had an average value of
282 1.75 GPa and 1.85 GPa for E' and E^* respectively. No statistically significant difference
283 ($p=0.05$, by t-test) could be found between this and the 4, 8 or 11 day exposure period,
284 however the 4 day exposed samples appeared to gain rather than lose strength. The
285 longest exposure period, 17 days, appeared to lose strength relative to the control and
286 the shorter decay intervals.

287

288 [Figure 3a]

289

290 [Figure 3b]

291 **Figure 3 (a) Loss Modulus and (b) Complex Modulus for samples exposed to *Poria***
292 ***placenta* for 0, 4, 8, 11 and 17 days. Average of three samples per exposure period,**
293 **and error bars represent standard deviation.**

294

295

296

297 Comparison of the change in mean storage modulus at each exposure duration with the
298 mean quantity of fungal gDNA isolated shows a negative correlation between the two
299 variables (Figure 4, $R^2 = 0.9776$). While the standard deviation for both *P. placenta* gDNA
300 and modulus data remains high, this indicates that further study with increased
301 replication may yield further insight into the initial brown rot decay and change in
302 mechanical properties.

303

304

305 **Figure 4: Comparison of storage modulus with amount of fungal DNA isolated for**
306 **the four exposure periods. Error bars represent one standard deviation of the**
307 **mean.**

308

309 **4. Conclusion**

310 The paper reports the effects of initial on-set decay and the presence of fungal DNA
311 within the timber on the storage modulus of the timber. A correlation between observed
312 stiffness and the onset of decay as indicated by the fungal gDNA quantification technique

313 has been found. This paper establishes dynamic mechanical analysis as a technique for
314 the assessment of the effects of early on-set decay on the storage modulus of timber.

315

316

317 **Acknowledgements**

318 The authors of the paper would like to acknowledge COST Action FP 1407 for the
319 funding of a Short Term Scientific Mission for Dr. Graham Ormondroyd to visit NIBIO in
320 Norway and also the institute for their very generous hosting throughout his visit,
321 particularly Sigrun Kolstad for her patience in the teaching of new techniques to Dr
322 Ormondroyd.

323 Authors Ormondroyd, Curling, Spear and Prabhakaran acknowledge the financial
324 support provided by the Welsh Government and Higher Education Funding Council for
325 Wales through the Sêr Cymru National Research Network for Low Carbon, Energy and
326 Environment.

327

328 **References**

329 Alfredsen, G., Pilgård, A., Fossdal, C.G., 2016. Characterisation of *Postia placenta*
330 colonisation during 36 weeks in acetylated southern yellow pine sapwood at three
331 acetylation levels including genomic DNA and gene expression quantification of the
332 fungus. *Holzforschung*. DOI: 10.1515/hf-2015-0203.

333 Alfredsen, G., Pilgård, A., 2013. *Postia placenta* decay of acetic anhydride modified wood
334 – effect of leaching. *Wood Material Science & Engineering* 9(3), 162-169.

335 Alfredsen, G., Ringman, R., Pilgård, A., Fossdal, C.G., 2015. New insight regarding mode of
336 action of brown rot decay of modified wood based on DNA and gene expression studies:
337 A review. *International Wood Products Journal* 6(1), 5-7.

338 Arantes, V., Jellison, J., Goodell, B., 2012. Peculiarities of brown-rot fungi and biochemical
339 Fenton reaction with regard to their potential as a model for bioprocessing biomass.
340 *Applied Microbiology and Biotechnology* 94, 323-338.

341 Arantes, V., Goodell, B., 2014. Current understanding of brown-rot fungal biodegradation
342 mechanisms: A Review. In: *Deterioration and Protection of Sustainable Biomaterials*. Eds.
343 Nicholas, D.D., Goodell, B., Schultz, T. ACS Series. Oxford University Press, New York,
344 USA, Vol. 1158, pp. 3–21.

345 Baldrian, P., Valaskova, V., 2008, Degradation of cellulose by basidiomycetous fungi.
346 *FEMS Microbiology Reviews*, 32, 501-521.

347 Becker, H., Noack, D., 1968. Studies on dynamic viscoelasticity of wood. *Wood Science*
348 *and Technology* 2:213-230.

349 Birkinshaw, C., Buggy, M., Henn, G.G., 1986. Dynamic mechanical analysis of wood.
350 *Journal of Materials Science Letters* 5, 898-900.

351 CEN (1996) EN 113:1996/A1:2004 Wood preservatives - Test method for determining
352 the protective effectiveness against wood destroying basidiomycetes - Determination of
353 the toxic values. CEN (European committee for standardization), Brussels

- 354 Cowling, E.B., 1961. Comparative biochemistry of the decay of sweetgum by white-rot
355 and brown-rot fungi. USDA Technical Bulletin, Washington DC, USA.
- 356 Coyne, K.J., Handy, S.M., Demir, E., Whereat, E.B., Hutchins, D.A., Portune, K.J., Doblin,
357 M.A., Cary, S.C., 2005. Improved quantitative real-time PCR assays for enumeration of
358 harmful algal species in field samples using an exogenous DNA reference standard.
359 *Limnology and Oceanography-Methods* 3, 381–391.
- 360 Curling, S., Clausen, C.A., Winandy, J.E., 2002. Relationships between mechanical
361 properties, weight loss and chemical composition of wood during incipient brown rot
362 decay. *Forest Products Journal*, 52 (7-8), 34-39.
- 363 Eikenes, M., Alfredsen, G., Christensen, B.E., Militz, H., Solheim, H., 2005. Comparison of
364 chitosan with different molecular weights as possible wood preservative. *Journal of*
365 *Wood Science* 51: 387-394.
- 366 Goodell, B., Daniel, G., Jellison, J., Qian, Y., 2006. Iron-reducing capacity of low molecular
367 weight compounds produced in wood by fungi. *Holzforschung* 60, 630-636.
- 368 Goodell, B., Jellison, J., Liu, J., Daniel, G., Paszczynski, A., Fekete, F., Krishnamurthy, S., Jun,
369 L., Xu, G., 1997. Low molecular weight chelators and phenolic compounds isolated from
370 wood decay fungi and their role in the fungal biodegradation of wood. *Journal of*
371 *Biotechnology* 52, 133-162.
- 372 Green, F., Highley, T.L., 1997. Mechanism of brown rot decay: paradigm or paradox.
373 *International Biodeterioration & Biodegradation* 39, 113-124.
- 374 Hietala, A., Stefańczyk, E., Nagy, N.E., Fossdal, C.G., Alfredsen, G., 2014. The suppressive
375 effect of high temperature on wood decay caused by the brown-rot fungus *Postia*
376 *placenta* depends on wood durability. *Holzforschung* 68(1), 123–131.
- 377 Hill, C.A.S., Hale, M.D., Ormondroyd, G.A., Kwon, J.H. Forster, S.C. 2006. Decay resistance
378 of anhydride-modified Corsican pine sapwood exposed to the brown rot fungus
379 *Coniophora puteana*. *Holzforschung* 60 625-629
- 380 Hillis, W.E., Rozsa, A.N., 1985. High Temperature and chemical affects on wood stability
381 Part 2: The effect of heat on the softening of radiata pine. *Wood Science and Technology*
382 19, 57-66.
- 383 Hillis, W.E., Rozsa, A.N., 1978. The softening temperatures of wood. *Holzforschung*
384 32:68-78.
- 385 Jellison, J., Goodall, B., Alfredsen, G., Eastwood, D., Daniel, G., Cragg, S.M., Grace, J.K., 2013.
386 What molecular biology can tell us about the biodegradation of lignocellulose: the
387 utilization of molecular techniques for the detection, identification and enhanced
388 understanding of wood degrading organisms. In: Proceedings of IRG Annual meeting
389 2013 IRG/WP 13-20528 16-20 June 2013 Stockholm, Sweden.
- 390 Kelley, S.S., Rials, T.G., Glasser, W.G., 1987. Relaxation behavior of the amorphous
391 components of wood. *Journal of Materials Science*, 22:617-622.
- 392 McCarthy, C.J., Birkinshaw, C., Penbroke, J.T., Hale, M., 1991. Dynamic mechanical
393 analysis as a technique for the study of fungal degradation of wood. *Biotechnology*
394 *Techniques* 5(6), 493-496.

395 Monrroy, M., Ortega, I., Ramirez, M., Baeza, J., Freer, J., 2011. Structural change in wood
396 by brown rot fungi and effect on enzymatic hydrolysis. *Enzyme and Microbial*
397 *Technology* 49, 472-477.

398 Norimoto, M., Yamada, T., 1966. Dynamic Torsion viscoelasticity of wood. *Wood*
399 *Research* 38, 32-39.

400 Olsson, A.-M., Salmén L., 2004. The softening behavior of hemicelluloses related to
401 moisture. In: *Hemicellulose: Science and Technology*, Eds. Gatenholm, P., Tenkanen, M.,
402 American Chemical Society, Washington DC, USA. pp. 184-196.

403 Pilgård, A., Alfredsen, G., Björdal, C.G., Børja, I., Fossdal, C.G., 2011. qPCR as a tool to
404 study basidiomycete colonization in wooden field stakes. *Holzforschung* 65, 889-895.

405 Ray, M.J., Leak, D.J., Spanu, P.D., Murphy, R.J., 2010. Brown rot fungal early stage decay
406 mechanism as a biological pretreatment for softwood in biofuel production. *Biomass*
407 *and Bioenergy* 34, 1257-1262.

408 Ringman, R., Pilgård, A., Richter, K., 2014. Effect of wood modification on gene
409 expression during incipient *Postia placenta* decay. *International Biodeterioration &*
410 *Biodegradation* 86, 86-91

411 Salmén, L., Olsson, A.-M., 1998. Interactions between hemicellulose, lignin and cellulose:
412 Structure-property relationships. *Journal of Pulp and Paper Science* 24, 1049-1056.

413 Sun, N. Das, S., Frazier, C.E. (2007) Dynamic mechanical analysis of dry wood: Linear
414 viscoelastic response region and effects of minor moisture changes. *Holzforschung* 61,
415 28-33.

416 Wilson, T.C.R., 1932. Strength-Moisture Relations for Wood. Technical Bulletin no. 282.
417 United States Department of Agriculture, Washington DC. 88 p.

418 S. L. Zelinka, R. Ringman, A. Pilgård, E. E. Thybring, J. E. Jakes & K. Richter (2016) The
419 role of chemical transport in the brown-rot decay resistance of modified wood,
420 *International Wood Products Journal*, 7:2, 66-70

421