

Emissions from bio-based building products

Clauder, Lothar; Ormondroyd, Graham; Mansour, Elie; Pfriem, Alexander

COST FP1303 Design, Application and Aesthetics of biobased building materials

Published: 01/03/2017

Peer reviewed version

Cyswllt i'r cyhoeddiad / Link to publication

Dyfyniad o'r fersiwn a gyhoeddwyd / Citation for published version (APA): Clauder, L., Ormondroyd, G., Mansour, E., & Pfriem, A. (2017). Emissions from bio-based building products. In COST FP1303 Design, Application and Aesthetics of biobased building materials (pp. 1-2).

Hawliau Cyffredinol / General rights Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

· Users may download and print one copy of any publication from the public portal for the purpose of private study or research.

- You may not further distribute the material or use it for any profit-making activity or commercial gain
 You may freely distribute the URL identifying the publication in the public portal ?

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Emissions from bio-based building products

- L. Clauder¹, E. Mansour², G. Ormondroyd², A. Pfriem¹
- ¹ Eberswalde University for Sustainable Development, Germany, Lothar.Clauder@hnee.de, Alexander.Pfriem@hnee.de
- ² BioComposites Centre, Bangor University, United Kingdom, g.ormondroyd@bangor.ac.uk, e.mansour@bangor.ac.uk

Keywords: corrosion, emissions, volatile organic compounds

The study focused on the emission behaviour of wood and the occurrence of corrosion on lead coupons due to these emissions when both materials were combined in a modified Oddytest (Oddy 1973, modified). Wood may not seem like a challenging environment for corrosion but by its porous micro- and ultrastructure wood has complex interactions with water that greatly affects its physical, mechanical, and chemical properties, including corrosion (Zelinka 2014). Wood can be considered as one of the major emission sources of formaldehyde and other volatile compounds. During the kiln drying of wood, the hydrolysis of cell wall components (cellulose, hemicellulose and lignin) leads to formation of furfural, formaldehyde and very volatile acids, e.g. acetic and formic acid. In addition, at a relative humidity of 20 % an initial molecular layer of water on the metal surface can react with atmospheric formaldehyde to produce formic acid which in turn causes metal corrosion (Hatchfield et al. 1986).

The selected test set up consisted of wood species which are known to have low emissions such as Alder, and wood species with expected higher emission rates such as Ash and Oak. Six samples of each species were impregnated with a buffer-solution and were dried under vacuum conditions along with further six untreated samples to an absolute dry state. According to Cole (1979) a pH range of 3.3 to 7.2 for hardwoods (e.g. 5.5 for Alder and 3.3 to 3.9 for Oak) was found. All pH measurements were made with a WTW pH meter, Model inoLab according to the technique of Lambuth (1967). In this study the measurements of the emissions from wood were performed based on ISO 16000-10 (2006) with a micro-chamber. Specimens were installed under constant conditions with respect to temperature, relative humidity and air exchange rates. The samples were prepared according to ISO 16000-11, formatted (\emptyset 40 mm) and stored in a conditioning room (23 ± 2 °C and 50 ± 5 %). Prior to the tests, fresh surfaces were planed. The stainless steel cell allowed a controlled climate at 23 ± 1 °C and 50 ± 3 % RH. Using the Oddy test (Oddy 1973), potential damage of art objects through formaldehyde and organic acid (formic and acetic) vapour is seen to accelerate by the addition of a small amount of water (1 ml), elevation of

temperature to 60 °C and storage for 28 days; this prompts the evolution of potentially corrosive gases from the test material and metal corrosion reactions.

The impregnation with the buffer solution led to the intended effect. The results showed that the buffer system with a pH value of 7.2 caused an increase of the pH values of the three different species: Alder (6.22 to 6.65), Oak 4.72 to 5.27) and Ash (5.82 to 6.82). The subsequently performed investigations of the emissions and the degree of corrosiveness were affected by the decreased acidity of the specimens (Fig. 1).



Figure 1: left: Sum of emissions of aldehydes consisting of C>2 (i.e. furfural, hexanal, heptanal, octanal, nonanal and decanal) AN = Ash untreated, A = Ash impreg., ON = Oak ut, O = Oak i., ALN = Alder ut, AL = Alder i.; right: lead coupons removed from Oddy test-vessel

The results indicated the positive influence of the buffer treatment on the chemical compounds. However, acet-, formaldehyde and VOCs possess very little corrosiveness towards materials like textiles, paper and metals. By contrast, vapours of organic acids (formic and acetic acid) are known to be reactants in the metal corrosion. This became visible after the Oddy tests when lead coupons were removed from the test vessels. Due to increased amounts of water available in the vessel, the results became more pronounced to the point of being rated as unsuitable because of heavy corrosions. Possibly usage of biobased products is limited in sensitive environment.

References

- Cole, H.C., Chandler, K.A., Bernie, J.A., Leach, L., Parkins, R.N., Pequinot, C.A., Shrier, L., Smith, T.J. (1979): Guides to practice in Corrosion Control, Corrosion of metals by wood, Corrosion Centre Wales, Newport, Wales.
- Hatchfield, P.B., Carpenter, J.M. (1986): The problem of formaldehyde in museum collections, In: International Journal of Museum Management and Curatorship, 5 (2), pp. 183- 188, DOI: 10.1080/09647778609515020
- Lambuth, A.L. (1967): Procedure for determining the pH and buffering capacity of wood. Lab Test Method No. 142, Monsanto Company Seattle Research.
- Oddy, W.A. (1973): An unsuspected danger in display, In: Museums journal 73, pp. 27-28.
- ISO 16000 (2006): Indoor air Determination of the emission of volatile organic compounds from building products and furnishing Part 10: Emission test cell method, Part 10: Sampling, storage of samples and preparation of test specimens.
- Zelinka, S., Glass, V., Stone, D. (2008): A percolation model for electrical conduction in wood with implications for wood-water relations. In: Wood and Fiber Science 40(4), pp. 544-552.

Acknowledgments: The authors gratefully acknowledge the financial support of the COST action FP1303 for the STSM.