Fibre degradation of wheat straw by *Pleurotus eryngii* under low moisture conditions during solid-state fermentation

Baker, P. W.; Charlton, A.; Hale, M. D. C.

Letters in Applied Microbiology

DOI:
[10.1111/lam.13104](https://doi.org/10.1111/lam.13104)

Published: 01/02/2019

Peer reviewed version

[Cyswllt i'r cyhoeddiad / Link to publication](#)

Dyfyniad o'r fersiwn a gyhoeddwyd / Citation for published version (APA):
Baker, P. W., Charlton, A., & Hale, M. D. C. (2019). Fibre degradation of wheat straw by *Pleurotus eryngii* under low moisture conditions during solid-state fermentation. *Letters in Applied Microbiology*, 68(2), 182-187. <https://doi.org/10.1111/lam.13104>

Hawliau Cyffredinol / General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal ?

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Fibre degradation of wheat straw by *Pleurotus eryngii* under low moisture conditions during solid state fermentation

Paul W. Baker^{*1}, Adam Charlton² Mike D.C. Hale¹

Email: paul.baker@bangor.ac.uk

Tel: 0044 (0)1248-382540

Paul Baker (*) · Adam Charlton

BioComposites, Bangor University, Deiniol Road, Bangor, Gwynedd LL57 2UW, UK

Mike Hale

School of Environment, Natural Resources and Geography, Bangor University, Bangor, Gwynedd, LL57 2UW, UK

Running Title: Fungal decomposing wheat straw under low moisture

Significance and Impact of the Study

In this study, a white rot fungus, *P. eryngii*, effectively decomposed fibre under low moisture conditions when grown on wheat straw at similar levels under higher moisture conditions. However, the addition of wheat bran to wheat straw created a heterogenous system that appeared to allow *P. eryngii* to thrive under much lower moisture conditions although lower levels of fibre decomposition was obtained. These factors could influence the preparation of solid state fermentation.

Abstract

The application of solid state fermentation offers an alternative to conventional, submerged approaches for a variety of bioconversion processes, including animal feeds, biofuels and fungal bioproducts. Optimising solid state fermentation under low moisture conditions could significantly impact the proportion of dry biomass that

could be processed and improve the commercial viability of this approach, because of reduced input costs and higher yields of final products. *Pleurotus eryngii* that appeared to show tolerance to low moisture conditions was grown on saturated and desaturated wheat straw. *P. eryngii* showed insignificant fibre degradation although showed significantly lower biomass decomposition on desaturated wheat straw. Fibre decomposition by the fungus on wheat straw containing wheat bran showed marginally higher decomposition when saturated although there was no difference in biomass decomposition. The levels of delignification achieved were similar under different saturation conditions. It would appear that the fungus effectively decomposed fibre under low moisture conditions often resulting in lower biomass losses.

Keywords

moisture content · wheat straw · *Pleurotus* · evaporation · solid state fermentation

Introduction

Wood rot fungi that have a high tolerance to low moisture conditions with the ability to grow at much higher solid to liquid ratios could have useful applications in solid state fermentation of agricultural waste products (Wan and Li 2012). Some of the benefits would be lower energy requirements to regulate the temperature of the fermentation, which could significantly increase with larger quantities of waste and the opportunity to extract desirable products using organic solvents (Vamanu 2014). Most studies using agricultural waste substrates reveal that higher moisture contents support optimal growth of wood rot fungi (Asgher *et al.* 2006; Shi *et al.* 2008), leading to significantly higher levels of lignin degradation (Shi *et al.* 2008). Many of these studies have focused on the Basidiomycetes, *Phanerochaete chrysosporium*, *Lentinus edodes* and *Cereporiopsis subvermispora*, which showed a direct correlation between growth rate and water potential (Badham 1989; Boddy 1983; Wan and Li 2012). An evaluation of a wider range of Basidiomycetes has shown that each has a specific and different set of moisture conditions, which support optimum growth between 65-85% moisture condition and only one fungus grew optimally at a low moisture condition of 50-65% (Zadražil and Brunnert 1981). It has been suggested that fungi associated with dried fallen stems are most likely to exhibit higher tolerance to water stress conditions (Boddy 1983). Surprisingly, natural isolates of *Trametes* sp. and *Collybia sierraleonis* recovered from tropical regions did not show any increased level of tolerance to water stress

conditions compared with fungal strains recovered from temporal regions (Mswaka and Magan 1999; Singh 1989).

Wheat straw that has been pre-processed using some form of milling process contains vessels which, through capillary action, may draw water inside the plant matrix and the non-homogenous structure of this substrate (haphazardly arranged and different sized straw fragments) will ensure that there are spaces allowing gaseous exchange. However, wheat bran does not have the vessel structures but fine granular structure requires lower moisture conditions for higher enzymatic production as shown by the Ascomycete, *Trichoderma longibrachiatum* in producing xylanase (Azin *et al.* 2007), by the Ascomycete, *Aspergillus* sp. in producing cellulase (Vu *et al.* 2011) and by white rot fungus, *Pleurotus pulmonarius* in producing manganese peroxidase (Farani de Souza *et al.* 2006). Presumably, the granular composition of wheat bran causes the particles to become more closely associated, thus limiting the volume of space being formed between the bran particles that would allow gaseous exchange. Such high saturation conditions would have a negative influence on gas diffusion and perhaps other parameters such as enzyme activities, temperature regulation, and substrate inhibition (Gervais and Molin 2003). This is supported in a previous study showing that steady low levels of aeration are required in order to achieve significant rates of delignification (López *et al.* 2002).

The aim of this study was to determine the degradation characteristics of saturated and desaturated wheat straw by fungi, which showed quite high tolerance to low moisture conditions. The saturated wheat straw contains freely available water within the plants vessels allowing optimal fungal growth. In contrast, it is presumed that the desaturated wheat straw contains little free water except in the narrowest plant vessels. The availability of free water and bound water will have an impact on microbial utilization (Magan 2007). Fungi were selected based on a prior experiment revealing that *P. erygnii* showed quite high tolerance to low moisture conditions compared with other white rot fungi, while *P. pycnoporus* was somewhat tolerant (Baker, unpublished).

Results and discussion

The initial trial showed that *P. erygnii* and *G. tsugae* completely colonized the wheat straw, although *P. erygnii* showed greater changes in the fibre composition. Three fungi showed only partial colonization but showed fibre decomposition in the following decreasing order: *G. resinaceum*, *L. edodes*, and *P. sanguineus*. In a previous

study, it was shown that *L. edodes* was quite tolerant to water stress conditions when grown on wood rather than glycerol amended medium (Badham 1989). In our study, *G. australe*, *P. ostreatus* and *C. subvermispora* failed to colonize the wheat straw. This study was performed using smaller Microsacs with filter seams in closer proximity to the substrate may have resulted in the significant decrease in moisture content of the wheat straw. Therefore, only fungi which rapidly grew may have completely colonized the wheat straw.

The saturated and desaturated wheat straw substrate, containing mineral nutrients, was inoculated with similar quantities at 41.2 ± 1.5 g and 48.8 ± 11.2 g of *P. eryngii* infected grain, respectively. It can be assumed that the wheat straw that now has a lower moisture content because some of the water previously associated with wheat straw was absorbed by wheat bran. It is possible that the addition of moist infected grain may allow moisture to be translocated by the mycelium to as shown in a previous study in the fungal degradation of stacked wood blocks (Stienen *et al.* 2014). The moisture contents of the saturated and the desaturated wheat straw at the start of the experiment were significantly different ($P = 0.0004$) and the moisture content decreased significantly by the end of the experiment in the saturated wheat straw ($P = 0.009$), whereas the moisture content in the desaturated wheat straw remained unchanged (Table 1). The expectation would be that the moisture content would increase as fungal degradation proceeds, but unlike wood, the fragments of wheat straw would allow for evaporation that would offset the possible increase in moisture content. A direct comparison with the data in another study revealed that these moisture contents lie within the optimal range (Zadrazil and Brunnert 1981), where the optimum may be midway (Saha *et al.* 2017). Fungal degradation significantly decreased the total dry weight by $18.0 \pm 3.0\%$ in saturated wheat straw and by $11.0 \pm 2.0\%$ in desaturated wheat straw ($P = 0.03$). As expected, the fibre composition in the saturated and desaturated experiments at the start was similar (Table 2) and there were no significant differences in fibre composition between saturated and desaturated wheat straw at the end of the experiment after fungal degradation. The fibre composition showed some significant changes after fungal degradation, which differed under both saturation conditions compared with the undegraded wheat straw at the start. It would be expected that after such a long incubation period where the fungus had completely colonized the substrate that differences in fibre composition would be found, if there were any, under the different treatments. It is uncertain whether a longer incubation would have shown differences. Similar levels of delignification occurred under saturated and desaturated conditions and the total percentage of lignin degraded was slightly higher (Table 3).

Similar quantities of *P. eryngii* infected grain were inoculated into wheat straw containing wheat bran with 17.8 ± 2.1 g under saturated conditions and with 23.0 ± 4.5 g under desaturated conditions. The moisture

contents of saturated and desaturated wheat straw at the start of the experiment were significantly different ($P = 0.007$) and the moisture contents remained unchanged until the end of the experiment (Table 1). A direct comparison with a previous study showed that the moisture contents of the desaturated wheat straw was just below the lowest limit examined where degradation and delignification was restricted for most white rot fungi (Zadražil and Brunnert 1981). The moisture contents of wheat straw containing wheat bran were significantly lower compared with wheat straw containing mineral salts ($P < 0.01$) under both saturation conditions and presented much lower moisture conditions. However, the optimal moisture conditions for fungal growth on wheat bran are lower (Farani de Souza *et al.* 2006) compared with wheat straw and wheat bran may support the initial stages of fungal growth. The addition of wheat bran to wheat straw at the start of the experiment revealed that the proportion of non-fibre had significantly increased, whereas the proportion of cellulose had decreased in comparison to the experiments containing only wheat straw (Table 2). The degradation in terms of dry weights by *P. erygnii* in saturated and desaturated wheat straw were $14.1 \pm 5.1\%$ and $6.7 \pm 5.6\%$, but these were not significant different. Fungal degradation resulted in significant compositional changes in the straw, causing an increase in the non fibre content ($P = 0.046$) and a decrease in the hemicellulose content ($P = 0.003$) under saturated conditions compared with desaturated conditions (Table 2). Although a constant amount of wheat bran (72 g) was added to 250 g of wet wheat straw (saturated or desaturated), wheat bran formed $50.9 \pm 2.8\%$ of the total dry weight under saturated conditions and $37.4 \pm 0.4\%$ of the total dry weight under desaturated conditions. Therefore, the proportion of wheat bran associated with saturated wheat straw was significantly greater ($P = 1 \times 10^{-6}$) and growth of *P. erygnii* appeared to be more favourable under saturated conditions. The addition of wheat bran appeared to have lowered the extent of delignification but this was not significantly different under saturated or desaturated conditions (Table 3). It is uncertain whether the lower levels of delignification were caused by using an easily accessible substrate, wheat bran, or by using lower quantities of grain inoculums. The total percentage of lignin degraded was higher in comparison to the percentage of delignification due to the higher biomass losses. *P. erygnii* appeared to cause similar levels of degradation under these water stress conditions compared with more saturated conditions, which is in contrast with most white rot fungi grown under slightly higher moisture conditions of 50% (Zadražil and Brunnert 1981).

The results confirmed those obtained from an initial trail showing that *P. erygnii* caused similar levels of fibre decomposition under both saturation conditions. The addition of dry wheat bran reduced the moisture content further but this did not affect fibre decomposition by either fungi even under the much lower

moisture conditions. The growth of fungi under lower moisture conditions would facilitate the extraction of compounds that require organic solvents and improve the operating conditions for solid-state fermentation.

Materials and methods

Preparation of fungal inoculum

A variety of fungi: *Ganoderma resinaceum* GR, *Ganoderma tsugae* XHMF, *Ganoderma australe* GA1, *Lentinus edodes* CYN, *Pleurotus erygnii*, *Pycnoporus sanguineus* V and *Pleurotus ostreatus* Pox K from the Bangor University culture collection and *Ceriporiopsis subvermispora* D98698 from the VTT (Finland) culture collection were grown on desaturated wheat containing mineral solution in an environmentally controlled room during an initial trial. An initial trial was performed to determine which fungi grew under low moisture conditions using Microsacs (49 cm x 22 cm with 5 filter seams – 4 on one side and 1 on the other). This experiment was repeated in triplicate based on the trial using *P. erygnii* which grew well under low moisture conditions. These fungus was first grown on 2% malt extract agar. A 5 mm² square was excised from the edge of the fungal colony that had been growing on 2% malt extract agar for one week at 22 °C and inoculated into autoclave sterilised (121 °C, 15 min) mushroom spawn bags (Microsac, SacO₂, Belgium). Each Microsac (49 cm x 22 cm with 5 aeration filter seams) containing 200 g wheat grain, 1.2 g calcium sulphate and 220 ml distilled water, were heat sealed and incubated for 3 weeks at 22 °C.

Preparation of Microsacs containing wheat straw and mineral nutrients

The substrate was prepared by soaking air dried hammermilled wheat straw that was collected through 5-10 mm screens (2 kg), in mineral solution [10 L, containing 2 g L⁻¹ ammonium chloride, 0.5 g L⁻¹, magnesium sulphate, 0.2 g L⁻¹ potassium dihydrogen phosphate, 0.2 g L⁻¹ disodium hydrogen phosphate, 0.35 g L⁻¹ manganese sulphate, 0.007 g L⁻¹ ferrous sulphate, and 0.007 g L⁻¹ copper sulphate] at 80 °C for 30 min. After soaking, the excess liquid was allowed to freely drain through a sieve. Half of this wheat straw was used to prepare six Microsacs (40 cm x 51 cm with 4 filter seams) each containing saturated wheat straw (250 g) and the remaining wheat straw was used to determine moisture content.

The other half of the wheat straw was placed into a large cloth bag and centrifuged at 2800 rpm for 5 min (White Knight spin dryer) to obtain desaturated wheat straw. This wheat straw was distributed as 250 g into

each of six Microsacs and moisture content was determined using the remaining wheat straw. All of the Microsacs containing the wheat straw were autoclaved at 121 °C for 60 min which was demonstrated to have no effect on the moisture content. Once the substrate had equilibrated to room temperature, each Microsac was inoculated with 45.0 ± 8.3 g of fungus infected grain to roughly equal proportions as judged by eye with the aim of preparing the substrate bags relatively quickly to avoid potential contamination issues with an open spawn bag. Then the bags were heat sealed, thoroughly mixed and weighed again to determine the weight of grain added. The Microsacs were incubated at 22 °C, 65% relative humidity for 42 days for *P. eryngii* which reflected the time required for the fungus to completely colonize the wheat straw.

Preparation of Microsacs containing wheat straw and organic nutrients

Substrate was prepared by soaking air dried milled wheat straw (2 kg) in hot water (10 L) at 80 °C for 30 min and removing the excess by sieving. Half of this wheat straw was used to prepare six Microsacs each containing 250 g wet wheat straw, 73 g dry wheat bran (purchased from a health store and <2 mm diameter) and 11 g dry calcium sulphate which was thoroughly mixed. The other half of wheat straw was centrifuged at 2800 rpm for 5 min and 250 g of this desaturated wheat straw was placed into each of six Microsacs along with 73 g dry wheat bran and 11 g dry calcium sulphate which was thoroughly mixed. Each of the Microsacs were thoroughly mixed, autoclaved and once cooled, were inoculated with 20.4 ± 4.6 fungus infected wheat grain and weighed again to determine the weight of grain added. The Microsacs incubated at 22 °C for 21 days in a humidity controlled room at 65%. The addition of wheat bran to wheat straw enabled fungal colonization by both fungi to occur more rapidly compared to the previous experiments where only wheat straw was used.

Analysis of samples

The contents of each Microsac was thoroughly mixed and samples were collected at the start and at the end of the experiment to determine mass loss, moisture content and fibre composition. Fibre analysis was determined as previously described (Baker *et al.* 2015) although the lignin content was determined by incubating each of the Ankom Microfiber bags after ADF extraction in 72% (v/v) H₂SO₄ (5 ml) for 2 h at 22 °C, then adding distilled water (140 ml) and autoclaving for 1 h at 121 °C 15 p.s.i. Finally, the bags were dried at 103 °C for 24 h and weighed. The ash content was determined in the Microfiber bags by furnace drying the bags after NDF, ADF and lignin extraction at 600 °C for 4 h. The actual hemicellulose, cellulose and lignin contents were determined by subtracting the ash content after NDF, ADF and lignin extraction, respectively.

Determination of moisture content

The moisture content was determined on triplicate samples by oven drying at 70 °C for 24 h to a constant dry weight and calculating the difference of wet weight and dry weight divided by the wet weight which was then expressed as a percentage.

Statistical analysis

Statistical analysis of the calculated data was performed using Student's *t*-test and values with *P*<0.05 are described as statistically significant as described in the results and discussion. The data presented in the tables showing statistical differences were analysed using SPSS Statistics 22 by analysis of variance.

Acknowledgements

The authors would like to acknowledge support through the BEACON+ project, partially funded through the European Regional Development Fund by the Welsh Government.

Conflicts of interest

None of the authors has any conflict of interest in publishing this study.

References

218 Asgher, M., Asad, M.J., Legge, R.L. (2006) Enhanced lignin peroxidase synthesis by *Phanerochaete*
219 *Chrysosporium* in solid state bioprocessing of a lignocellulosic substrate. *World J. Microbiol. Biotechnol.*
220 **22**, 449–453.

221 Azin, M., Morvej, R., Zareh, D. (2007) Production of xylanase by *Trichoderma longibrachiatum* on a mixture
222 of wheat bran and wheat straw: Optimization of culture condition by Taguchi method. *Enzyme Microb.*
223 *Technol.* **40**, 801–805.

224 Baker, P.W., Charlton, A., Hale, M.D., 2015. Increased delignification by white rot fungi after pressure refining
225 *Miscanthus*. *Bioresour. Technol.* **189**, 81-86.

226 Badham, E.R. (1989) Influence of water potential on growth of Shitake mycelium. *Mycologia* **8**, 464-468.

227 Boddy, L., (1983) Effect of temperature and water potential on growth rate of wood-rotting Basidiomycetes.
228 *Trans. Br. Mycol. Soc.* **80**, 141-149.

229 de Souza, D.F., Tychanowicz, G.K., de Souza, C.G., Peralta, R.M. (2006) Co-production of ligninolytic
230 enzymes by *Pleurotus pulmonarius* on wheat bran solid state cultures. *J. Basic Microbiol.* **46**, 126-134.

231 Gervais, P., Molin, P. (2003) The role of water in solid-state fermentation. *Biochem. Eng. J.* **13**, 85–101.

232 López, M.J., Elorrieta, M.A., Vargas-García, M.C., Suárez-Estrella, F., Moreno, J. (2002) The effect of aeration
233 on the biotransformation of lignocellulosic wastes by white-rot fungi. *Bioresour. Technol.* **81**, 123-129.

234 Magan, N. (2007) Fungi in Extreme Environments. In: Kubicek, C., Druzhinina, I. (Eds) Environmental and
235 Microbial Relationships. The Mycota, Vol. 4. Springer, Berlin, Heidelberg

236 Mswaka, A.Y., Magan, N. (1999) Temperature and water potential relations of tropical *Trametes* and other
237 wood-decay fungi from the indigenous forests of Zimbabwe. *Mycol. Res.* **103**, 1309-1317.

238 Saha, B.C., Kennedy, G.J., Qureshi, N., Cotta, M.A. (2017) Biological pretreatment of corn stover with *Phlebia*
239 *brevispora* NRRL-13108 for enhanced enzymatic hydrolysis and efficient ethanol production. *Biotechnol.*
240 *Progr.* **33**, 365-374.

241 Shi, J., Chinn, M.S., Sharma-Shivappa, R.R. (2008) Microbial pretreatment of cotton stalks by solid state
242 cultivation of *Phanerochaete chrysosporium*. *Bioresour. Technol.* **99**, 6556–6564.

243 Singh, N. (1989) Effect of temperature and water potential on growth of *Collybia sierraeonis*. *Mycol. Res.* **92**,
244 235-237.

245 Stienen, T., Schmidt, O., Huckfeldt, T. (2014) Wood decay by indoor basidiomycetes at different moisture and
246 temperature. *Holzforschung* **68**, 9–15.

247 Vamanu, E. (2014) Antioxidant properties of mushroom mycelia obtained by batch cultivation and tocopherol
 248 content affected by extraction procedures. *BioMed Res. Int.* 2014.

249 Vu, V.H., Pham, T.A., Kim, K. (2011) Improvement of fungal cellulase production by mutation and
 250 optimization of solid state fermentation. *Mycobiology* **39**, 20-25.

251 Wan, C., Li, Y. (2012) Fungal pretreatment of lignocellulosic biomass. *Biotechnol. Adv.* **30**, 1447-1457.

252 Zdražil, F., Brunnert, H. (1981) Investigation of physical parameters important for the solid state
 253 fermentation of straw by white rot fungi. *Eur. J. Appl. Microbiol. Biotechnol.* **11**, 183-188.

Zhu, Y., Zou, X., Shen, T., Shi, J., Zhao, J., Holmes, M., Li, G. (2016) Determination of total acid content and
 moisture content during solid-state fermentation processes using hyperspectral imaging. *J. Food Eng.* **174**,
 75-84.

Table 1 The moisture percentage of wheat straw inoculated with *P. eryngii* at the start and at the end **when supplemented** with mineral salts or with wheat bran.

	WS	WS + WB
saturated (at start)	78.7 ± 0.8 ^a	59.4 ± 0.8 ^c
saturated (at end)	75.5 ± 0.9 ^{ab}	63.4 ± 2.6 ^c
desaturated (at start)	67.0 ± 0.4 ^{bc}	44.6 ± 6.9 ^d
desaturated (at end)	67.4 ± 0.5 ^{bc}	46.7 ± 2.9 ^d

Means within a row lacking a common superscript differ (P < 0.05).

Table 2 Comparison of fungal degradation by *P. eryngii* for each of the fibre components under saturated (wet) and desaturated (dry) conditions at the start and end for wheat straw only (WS) or wheat straw with wheat bran (WS+WB). Samples were analysed on days 0 (D0), 21 (D21) and 42 (D42).

		non fibre	hemicellulose	cellulose	lignin	ash
WS	wet D0	19.6 ± 0.2 ^a	29.5 ± 0.5 ^a	41.2 ± 0.8 ^a	6.8 ± 0.5 ^a	4.1 ± 0.1 ^a
	wet D42	32.3 ± 3.2 ^b	22.2 ± 0.5 ^b	37.8 ± 2.7 ^a	4.7 ± 0.8 ^a	4.5 ± 0.1 ^a
	dry D0	19.0 ± 0.5 ^a	30.1 ± 1.0 ^a	41.3 ± 0.8 ^a	5.0 ± 2.6 ^a	3.9 ± 0.1 ^a
	dry D42	31.0 ± 0.1 ^b	21.3 ± 2.3 ^b	36.3 ± 4.1 ^{ab}	4.7 ± 1.5 ^a	4.4 ± 0.3 ^a
WS + WB	wet D0	38.4 ± 0.9 ^b	27.4 ± 0.5 ^a	21.3 ± 0.5 ^c	5.7 ± 0.8 ^a	7.1 ± 0.8 ^b
	wet D21	40.1 ± 1.8 ^b	21.5 ± 0.7 ^b	22.5 ± 1.8 ^c	5.4 ± 0.3 ^a	10.4 ± 1.0 ^c
	dry D0	31.6 ± 7.9 ^b	27.8 ± 1.6 ^a	24.7 ± 6.5 ^c	7.8 ± 1.8 ^a	8.1 ± 1.6 ^b
	dry D21	30.4 ± 3.6 ^b	28.3 ± 4.7 ^a	34.2 ± 14.7 ^{bc}	6.6 ± 0.8 ^a	8.2 ± 1.3 ^b

Means within a row lacking a common superscript differ (P < 0.05).

Table 3 Percentage of delignification and total lignin degradation by *P. eryngii* with respect to different fungal inocula contained within grain into wheat straw immersed in mineral salts (WS) and into wheat straw supplemented with wheat bran (WS+WB) under saturated and desaturated conditions.

		Inoculum weight (g)	Delignification (%)	Total lignin degraded (%)
WS	Saturated	41.2 ± 1.5 ^a	32.3 ± 11.5 ^a	33.3 ± 10.9 ^a
	Desaturated	48.8 ± 11.2 ^a	19.5 ± 14.4 ^a	29.4 ± 10.2 ^a
WS+WB	Saturated	16.9 ± 1.4 ^b	5.9 ± 6.1 ^a	17.9 ± 8.9 ^a
	Desaturated	23.0 ± 4.5 ^b	15.8 ± 10.5 ^a	19.8 ± 12.6 ^a

Means within a row lacking a common superscript differ ($P < 0.05$).