

Purification and polymerisation of microbial D-lactic acid from DDGS hydrolysates fermentation

Zaini, Nurul Aqilah Mohd; Chatzifragkou, Afroditi; Tverezovskiy, Viacheslav; Charalampopoulos, Dimitris

Biochemical Engineering Journal

DOI:
[10.1016/j.bej.2019.107265](https://doi.org/10.1016/j.bej.2019.107265)

Published: 15/10/2019

Peer reviewed version

[Cyswllt i'r cyhoeddiad / Link to publication](https://doi.org/10.1016/j.bej.2019.107265)

Dyfyniad o'r fersiwn a gyhoeddwyd / Citation for published version (APA):
Zaini, N. A. M., Chatzifragkou, A., Tverezovskiy, V., & Charalampopoulos, D. (2019). Purification and polymerisation of microbial D-lactic acid from DDGS hydrolysates fermentation. *Biochemical Engineering Journal*, 150, Article 107265. <https://doi.org/10.1016/j.bej.2019.107265>

Hawliau Cyffredinol / General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal ?

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

**Purification and polymerisation of microbial D-lactic acid from DDGS
hydrolysates fermentation**

Nurul Aqilah Mohd Zaini^{a,b}, Afroditi Chatzifragkou^a, Viacheslav Tverezovskiy^c, Dimitris
Charalampopoulos^{a*}

^a Department of Food and Nutritional Sciences, University of Reading, Whiteknights, PO
Box 226, Reading RG6 6AP, United Kingdom

^b Centre for Biotechnology and Functional Food, Faculty of Science and Technology,
Universiti Kebangsaan Malaysia, 43600 Bangi, Selangor, Malaysia

^c BioComposites Centre, Bangor University, Deiniol Road, Bangor, Gwynedd LL57 2UW,
United Kingdom

*Correspondence concerning this manuscript to Professor Dimitris Charalampopoulos, Department of
Food and Nutritional Sciences, University of Reading, e-mail: d.charalampopoulos@reading.ac.uk

Abstract

A multi-step process was developed for microbial D-lactic acid purification, followed by poly-D-lactic acid (PDLA) synthesis via azeotropic polycondensation process. Several anion exchange resins were screened for their binding capacity using model lactic acid solutions. Amberlite® IRA67 (weak base anion exchange resin) showed the highest lactic acid adsorption, with maximum adsorption capacity, q_{max} , of 136.11 mg lactic acid / g of resin, and was further selected to purify D-lactic acid from DDGS hydrolysates through a three-step process; (1) treatment with 7% w/v activated carbon, (2) acidification of fermentation broth (Amberlite® IRA120) and (3) adsorption of lactic acid by anion exchange (Amberlite® IRA67). At the end of the purification process, 80.4% (w/w) D-lactic acid was recovered with 91.8% (w/w) purity, indicating the effectiveness of the developed downstream process. Furthermore, a clear yellowish solid polymer with a molecular weight of 3010 Da was obtained, suitable for applications in biomedical and agricultural sectors.

Keywords: purification, activated carbon, ion exchange resin, poly-D-lactic acid, azeotropic polycondensation, DDGS

1. Introduction

The world demand for lactic acid has increased significantly over the past few years, as the application of polylactic acid (PLA), offers distinctive advantages over petroleum-based polymers. PLA is a biodegradable plastic that can be used in biomedical and pharmaceutical industries as surgical suture, tissue engineering scaffolds or as drug delivery tool [1]. In the early stages of commercialisation, PLA was only produced for biomedical device applications due to its high cost [2]. Nowadays, the application of PLA has expanded to the electric and electronic industries for the production of casings and circuit boards, as well as in food industry for the production of food packaging and cutlery materials [3, 4]. Currently, the main producers of PLA are NatureWorks® LLC under the trade name Ingeo™, Cereplast, Inc. (United States), Corbion Purac (Netherlands), Toray Industries (Japan) and Zhejiang Hisun Biomaterial Co., Ltd (China) [2]. Report by IHS Markit [5], predicted that PLA will be the leading application of lactic acid by 2020. PLA offers advantages over conventional petrochemical-derived plastics being biodegradable and compostable [2], and reduces the reliance on fossil fuel for the production of plastics [6]. Moreover, PLA production has a lower environmental impact compared to conventional petroleum derived polymers, as the carbon emissions and the energy consumption are reduced by 15 to 60% and 25 to 55%, respectively [7]. The low toxicity of PLA, along with its positive environmental characteristics, has rendered it an ideal material for application in various fields, including the food, biomedical and agricultural sector [6].

The production of PLA from agricultural **residues** represents a promising route for production, as such biomass is available at low cost, is accessible throughout the year and does not compete with food crops. For example, corn stover [8] and rice bran [9] have been identified as potential fermentation substrates for D-lactic acid production. However, the fermentation broths derived from renewable sources contain a mixture of compounds, including a variety of

sugars and proteins, polyphenols and organic acids, and thus require an effective downstream processing for the successful recovery of the targeted compound before being used as monomer for polymer synthesis [10].

Several downstream processing techniques such as ion exchange chromatography, precipitation, solvent extraction, distillation, nanofiltration, membrane extraction and electrodialysis have been investigated for the recovery and purification of lactic acid from fermentation broths [11-15]. Among these, adsorption by ion exchange offers a distinct advantage as it is a simple and relatively cheap process that offers product specificity, which leads to high purification yields [14, 16]. In organic acid separation, anion exchange resins are widely used. However, no specific conclusions on the optimum conditions for lactic acid binding have been drawn so far for anion exchange resins. For example, some researchers reported that a solution pH above the pKa of lactic acid (pKa lactic acid, 3.86) give the highest binding of lactic acid to Amberlite® IRA67 [17], Amberlite® IRA96 [16] and Amberlite® IRA92 [18]. On the other hand, other studies have found that a pH below the pKa value give the highest adsorption of lactic acid and other carboxylic acids to Amberlite® IRA67 [19], Amberlite® IRA35 [20, 21] and Lewatit S3428 resins [22]. To promote lactic acid binding on an anionic resin below the pKa value, the fermentation broth was acidified by treatment with strong acid or by passing the broth through a strong acidic cation exchange resin, i.e. Duolite C-464, to convert lactate salt to lactic acid [21].

Ring opening polymerisation and direct polycondensation are the most common methods used to synthesise PLA from lactic acid. In ring opening polymerisation, PLA is polymerised through a cyclic lactide intermediate. Companies such as NatureWorks® LLC (United States) and Corbion N.V. (Netherlands), produce PLA through this route [4, 23, 24]. This protocol is of interest as it produces high molecular weight PLA. However, the procedure is complicated and time consuming because it involves several polymerisation steps and

requires high purity of the lactide monomer prior to PLA synthesis [25]. On the other hand, direct polycondensation offers significant advantages as the polymerisation process is simpler and easier in this case. In direct polycondensation, only one step for polymer synthesis is involved, during which the lactic acid solution is heated at 130 – 140 °C. Through this process, normally low molecular weight PLA (< 5000 Da) is produced with relatively weak mechanical properties; this is due to difficulties in removing the water from the reaction mixture as the polymerisation process progresses [26]. However, Ajioka, Enomoto, Suzuki and Yamaguchi [27] successfully produced high molecular weight PLA (> 300000 Da) using a single step synthesis using organic solvent with a catalyst (tin, Sn, powder) in azeotropic condition. Azeotropic polycondensation involved refluxing of the solvent under reduced pressure to remove the condensation water that was generated during polymer synthesis. This method had been patented and used by Mitsui Toatsu Chemicals (Japan) to synthesise PLA under the commercial name LACEA [6, 23].

The aim of the study was to develop a multi-step process for the purification of D-lactic acid from a fermentation broth based on dried distiller's grains with solubles (DDGS) hydrolysate [28]. Subsequently, the purified D-lactic acid was used as monomer for PDLA synthesis by employing an azeotropic polycondensation approach. As the purification of D-lactic acid from fermentation broth hydrolysates and its polymerisation process is rarely been reported, this study provides novel information on D-lactic acid separation, employing a multiple purification step followed by single step polymerisation process.

2. Materials and Methods

2.1 Materials

Dried Distillers Grains with Solubles (DDGS) was supplied from a bioethanol plant (Vivergo, Yorkshire, UK) and was alkaline pretreated as described by Zaini et al. [28]. Alkaline treated DDGS consisted of 52.6 g glucose, 25.0 g xylose, 10.3 g arabinose, and 0.04 g protein per 100 g of dried material. The resins (Amberlite® IRA67, Diaion® WA30, Amberlite® IRA400, Dowex® Marathon™ MSA and Amberlite® IRA120) and activated carbon used in this study were purchased from Sigma-Aldrich (US).

2.2 D-lactic acid production

D-lactic acid was produced by *L. coryniformis* subsp. *torquens* (DSM 20004) using a Simultaneous Saccharification and Fermentation (SSF) process of alkaline treated DDGS in a 2 L stirred tank bioreactor (Biostat B, Sartorius, Germany) [28]. The process was initiated by the simultaneous addition of Accellerase® 1500 (1 ml enzyme : 0.33 g cellulose) and *L. coryniformis* inoculum (starting OD of ~0.05) and was carried out for 30 hours (1.5 L fermentation medium). The SSF process was carried out at 37°C with an initial agitation speed of 250 rpm. The pH of fermentation medium was maintained at 5 with aseptic additions 5M NaOH and HCl through a peristaltic pump. The minimum dissolved oxygen (DO) level was kept at 20% by controlling automatically the stirrer speed. The culture containing the enzyme was inactivated by heat treatment at 95 °C for 10 minutes, followed by centrifugation at 17,105 *x g* for 20 minutes (4 °C). Supernatants containing D-lactic acid solutions were collected and kept at -20 °C for purification.

2.3 Resin preparation

Weak anion exchange resins (Amberlite® IRA67 and Diaion® WA30) and strong anion exchange resins (Amberlite® IRA400 and Dowex® Marathon™ MSA) were selected for this study. Before utilisation, the resins in free base form, were first converted to Cl⁻ form as described by [Moldes et al. \[29\]](#). Resins that were purchased in Cl⁻ form were only washed with distilled water [11, 30]. For the acidification of the fermentation broth, a cation exchange resin, Amberlite® IRA120, a strongly acidic resin in H⁺ form, was used. The resin was washed with distilled water three times to remove any contaminants. All resins were then oven dried at 50 °C overnight and stored at room temperature in closed containers before use. The properties of the ion exchange resins that were used in this study are presented in Table 1.

2.4 Screening and optimisation of anion exchange resins binding and recovery

For the screening experiments of the anion exchange resins, model lactic acid solutions were prepared using commercial lactic acid (85%, Food Chemical Codex, FCC, Sigma-Aldrich).

2.4.1 Effect of pH on lactic acid binding

The effect of pH on lactic acid binding was determined through batch experiments according to [Bishai et al. \[16\]](#) with slight modifications. 1 g of dried resin (Amberlite® IRA67, Diaion® WA30, Amberlite® IRA400 or Dowex® Marathon™ MSA) was mixed with 5 ml of lactic acid (50 g/l) at different initial pH conditions (2, 3, 4, 5, 6, 7 and 8) at 25 °C. The pH of the solutions was adjusted with 5 M NaOH. The mixtures were shaken at 200 rpm for 8 hours.

The liquid fractions from each mixture were collected by filtration and analysed for lactic acid concentration by HPLC.

2.4.2 Effect of temperature on lactic acid binding

In order to investigate the effect of temperature on lactic acid binding, 1 g of each dried resin (Amberlite[®] IRA67, Diaion[®] WA30, Amberlite[®] IRA400 or Dowex[®] Marathon[™] MSA) was mixed with 5 ml lactic acid (50 g/l), prepared at the optimum pH (obtained in Section 2.4.1) and incubated at temperatures of 25, 30, 40, 50 and 60 °C at 200 rpm. The mixtures were shaken at 200 rpm for 8 hours. The liquid fractions from each mixture were collected by filtration and analysed for lactic acid concentration by HPLC.

The binding capacity, q , and adsorption efficiency, E , of the resin at different pH and temperatures were calculated as follows, as described by Pradhan et al. [11]:

$$q = \frac{(C_i - C_f) * V}{R} \quad (1)$$

$$E = \frac{(C_i - C_f)}{C_i} * 100 \quad (2)$$

where, q is the amount of lactic acid adsorbed to the resin (mg/g), E is the efficiency of lactic acid binding (%), C_i is the initial concentration of lactic acid (g/l), C_f is the concentration of lactic acid after being mixed with the resin (g/l), V is the volume of lactic acid solution (l) and R is the weight of the resin (g).

2.4.3 Adsorption capacity of lactic acid by resins

Amberlite[®] IRA67 and Diaion[®] WA30 were selected to carry out adsorption isotherm analysis in batch operation as described by Bernardo et al. [31] and John et al. [17], with slight modifications. 1 g of each resin was mixed with 5 ml of lactic acid at various concentrations

(4 - 650 mg lactic acid per 5 ml). The initial pH of the lactic acid solutions was set taking into account their optimum binding pH (obtained in Section 2.4.1) for the respective resin. The reaction took place at optimum temperature (obtained in Section 2.4.2) at 200 rpm for 8 hours. Liquid samples from each mixture were filtered and collected for further analysis.

Three different nonlinear models, the Langmuir, Freundlich and Langmuir - Freundlich models, were then fitted to the data using Origin Pro 8.0 software (OriginLab, USA) [32] using the following equations:

$$\text{Langmuir model} \quad q = \frac{q_{max} * K * C}{K * C + 1} \quad (3)$$

$$\text{Freundlich model} \quad q = K_f * C^{\frac{1}{n}} \quad (4)$$

$$\text{Langmuir – Freundlich model} \quad \frac{q}{q_{max}} = \frac{K_{LF} * C^{nLF}}{1 + K_{LF} * C^{nLF}} \quad (5)$$

where, q is the amount of lactic acid adsorbed to the resin (mg/g), q_{max} is the maximum amount of lactic acid adsorbed to the resin (mg/g), K is the Langmuir adsorption constant, K_f is the Freundlich adsorption constant, K_{LF} is the affinity constant for adsorption, C is the amount of lactic acid (mg), n is the Freundlich adsorption constant and nLF is the Langmuir-Freundlich coefficient.

2.4.4 Effect of ionic strength of eluent (HCl) on lactic acid recovery

The resin that exhibited the highest binding capacity, q , (Amberlite® IRA67) was selected for further recovery experiments using HCl with different ionic strengths as eluent. 4 g of Amberlite® IRA67 were packed into a 100 mm (length) column (Fisher Scientific, Leicester, UK) and saturated with 20 ml of 30 g/l lactic acid solution. The resin was then washed with distilled water to remove any unbound lactic acid. Different concentrations of HCl

were used as eluent (0.05, 0.1, 0.5 and 1.0 M), which were passed down the packed column by gravity and fractions of effluents were collected (2 ml per fraction) at regular time intervals. All fractions were analysed for lactic acid concentration.

2.5 Purification of D-lactic acid from fermentation broth

2.5.1 Colour removal by activated carbon

The effect of activated carbon on the removal of the colour from the fermentation broth was determined. Powdered activated carbon was mixed with 5 ml of clarified fermentation broth at different loading concentrations (0, 1, 5, 7 and 10%, w/v), for 1.5 hours at 150 (25 °C). The mixture was then separated by centrifugation at $17,105 \times g$ for 10 minutes (4 °C). The pellet was washed twice with distilled water and the supernatants collected for sugar and lactic acid analysis.

2.5.2 Acidification of fermentation broth by cation exchange resin

After treatment with activated carbon, the fermentation broth was subjected to Amberlite® IRA 120, H⁺ resin aiming to convert sodium lactate into lactic acid [33]. 10 g of dried resin were packed into a 30 cm length Econo-glass column (i.d. 1 cm) which was first filled with distilled water and the height of the resin was fixed with a flow adaptor (i.d. 1 cm) (Biorad, California, US). Distilled water was allowed to pass through the column until the pH of effluent was around 6.5. Then, a constant flow of 3 ml/min using a peristaltic pump was applied. The fermentation broth containing sodium lactate with a pH around 5.5 was then pumped into the column at the same flow rate. When the pH of the effluent started to increase, the resin was considered saturated. Effluent fractions (4 ml each) were collected for lactic acid

and sugar analysis. Fractions containing D-lactic acid were pooled for subsequent purification. The resin was washed with distilled water to remove the remaining solution in interstitial spaces, regenerated with 1 M HCl and thoroughly rinsed with distilled water, before a new cycle [16].

2.5.3 Adsorption by anion exchange resin

Pooled supernatant fractions containing D-lactic acid were passed through an anion exchange resin, (Amberlite® IRA67) in fixed-bed column operation. 25 g of dried resin were packed into a 30 cm length Econo-glass column (i.d. 2.5 cm) which was first filled with distilled water and the upper side of resin was fixed with a flow adaptor (i.d. 2.5 cm). The system was washed with distilled water until the pH of the effluent was around 6.5. Then, the acidified broth obtained from Amberlite® IRA 120, H⁺ resin was pumped into the column at 3 ml/min. D-lactic acid was recovered with 0.5 M HCl. Fractions of effluents at each stage were collected (4 ml each) for lactic acid and sugar analysis.

2.6 Azeotropic polycondensation process of PDLA

Polycondensation of PDLA was conducted as described by Ajioka et al. [27] with minor modifications. 2 g of D-lactic acid were mixed with 40 ml toluene in 100 ml reaction flask, equipped with a Dean-stark apparatus and a magnetic stirrer. In the first step of the polycondensation process, the mixture was azeotropically dehydrated at 110 °C for 3 hours to remove the free water. After removing the condensed water that was trapped in the Dean-stark apparatus, the tube was packed with molecular sieve (4 Å) and calcium chloride in layers to remove small amounts of water dissolved in the organic solvent that was produced during PLA synthesis. 0.2 g tin (II)-2-ethylhexanoate (stannous octoate) was added to the reaction mixture

and then returned to reflux at 140 °C for another 80 hours. The polymer produced was then recovered by filtration and vacuum dried using Büchner funnel apparatus, followed by freeze drying (VisTis Sentry 2.0, Warminster, PA).

2.6 Analytical methods

The nitrogen content was determined using the Free Amino Nitrogen (FAN) method as described by Lie [34] with some modifications. 0.5 ml of diluted sample was mixed with 0.25 ml of colour reagent (49.71 g of Na₂HPO₄·2H₂O, 5 g of ninhydrin, 3 g of fructose and ~ 40 g of KH₂PO₄ dissolved in 1 l of distilled water; pH 6.6 – 6.8) in 2 ml Eppendorf tube. The mixture was heated at 100 °C in a thermal block (Grant, Cambridge) for exactly 16 minutes and immediately cooled in an ice bath. 1.5 ml of dilution reagent (2 g potassium iodate, KIO₃, in 616 ml distilled water and 384 ml 96% ethanol) was added and the free amino nitrogen content was measured at 570 nm. A calibration curve was constructed using glycine at different concentrations (0.25 – 2 mg/l) as standard.

Sugar and lactic acid concentrations were analysed by high performance liquid chromatography (HPLC) in an Agilent Infinity 1260 system (Agilent Technologies, USA) equipped with an Aminex HPX-87H column (Bio-rad, Hercules, CA) at a 0.6 ml/min flow rate with 5 mM H₂SO₄ as mobile phase. The temperature of the column was set at 65 °C and sugars and lactic acid were detected using a refractive index detector. The D-lactic acid recovery and purity were calculated using the following equations [16]:

$$Recovery (\%) = \frac{mg \text{ LA in each purification stage}}{mg \text{ LA in fermentation broth}} * 100 \quad (6)$$

$$Purity (\%) = \frac{HPLC \text{ peak area of LA in each purification stage}}{Total \text{ HPLC peak areas in each purification stage}} * 100 \quad (7)$$

The molecular weight and poly dispersity index (PDI) of PDLA was determined by gel permeation chromatography (GPC), using an Agilent 1100 Series chromatography system that was equipped with a refractive index RID 1200 detector (35 °C). The flow rate was set at 1.0 ml/min and the molecular size was determined using a PL gel 5 μ M mixed-D column (300 x 7.5 mm) and a PL gel 5 μ M guard column (50 x 7.5 mm). Chloroform was used as the eluent. The PDLA obtained was first dissolved in chloroform prior to analysis. The sample was analysed at room temperature using 20 μ l injection volume. A calibration curve was generated using polystyrene standards with molecular weights ranging from 580 to 483,400 Da.

3. Results and Discussion

3.1 Selection of anion exchange resin

When considering ion exchange chromatography, the efficiency of the product adsorption by the resin determines the success of the purification process. Therefore, factors such as pH, temperature and lactic acid concentration were initially investigated in this study in order to select the most appropriate anion exchange resin. The effect of the ionic strength of the eluent (HCl solution) on product recovery was also investigated. Before use, the resins that existed in free base were converted to Cl⁻ form. The Cl⁻ form was selected as previous studies have shown that in this form the resins exhibit the highest adsorption capacity for lactic acid [17, 31]. Moreover, the simultaneous lactic acid recovery and resin regeneration for subsequent adsorption cycles by HCl, reduces the number of steps involved in the purification process [29]. Four different resins, categorised into weak base anion exchange (Amberlite[®] IRA67 and Diaion[®] WA30) and strong base anion exchange (Amberlite[®] IRA400 and Dowex[®]

MarathonTM MSA) were tested against different initial pH values, ranging from 2 to 8, as shown in Figure 6a.

Among the tested resins, the weak base anion exchange resins showed capability for lactic acid binding at low pH, with the highest adsorption being 65% with Amberlite[®] IRA67 at pH 3, which corresponded to a maximum binding capacity (q_{max}) of 155 mg lactic acid/g of resin. For strong base anion exchange resins, less than 22% of lactic acid was adsorbed by both Amberlite[®] IRA400 and Dowex[®] MarathonTM MSA, with the highest binding at pH 6 and pH 4, respectively, suggesting that the pH did not influence the adsorption of lactic acid to the strong base anion exchange resins. On the other hand, the adsorption of weak base anion exchange resins was strongly influenced by the pH of the feed solution. In the case of Amberlite[®] IRA67 and Diaion[®] WA30, the best pH for lactic acid adsorption was below its pKa (3.86), where lactic acid exists in its undissociated form [21, 22, 35]. This can be associated with the charge of the tertiary amine (the functional group in both resins) which is cross-linked to the polymeric matrix (acrylic or styrene) in Amberlite[®] IRA67 and Diaion[®] WA30. It is assumed that the lone pair electron of the nitrogen atom in the tertiary amine is likely to hydrogen bond to lactic acid through the chloride ion [20, 36]. This mechanism is also supported by works from Yousuf et al. [35], Kislik [13] and Kulprathipanja and Oroskar [20], who reported that possible interactions between amine-based extractants and carboxylic acids are through hydrogen bonding, acid-base interaction, hydrophobic interaction, ion-ion pair formation or solvation.

Subsequently, the effect of temperature (25 to 60 °C) on lactic acid adsorption was investigated at pH values that were previously shown to give the highest lactic acid binding for each resin (Figure 6b). No differences were observed between the different temperatures, for each resin. As shown previously, the highest lactic acid adsorption (~73%) was exhibited by Amberlite[®] IRA67. According to Niazi and Brown [37], the effect of temperature on ion

exchange resins is mainly attributed to pKa changes of the targeted compound as a result of the temperature change. In the case of lactic acid, as the temperature increased from 25 to 30, 40 and 50°C, the pKa value also increased to 3.896, 3.942 and 4.028, respectively [38]. Since lactic acid adsorption to weak base anion exchange resins occurs below its pKa value, the increase in temperature from 25 to 60 °C did not have any significant effect.

3.1.1 Adsorption isotherms

The two resins that demonstrated the highest binding capacity, Amberlite® IRA67 and Diaion® WA30, were further tested. The adsorption isotherms were generated at 25 °C, and are shown in

Figure 7a and 2b, respectively. Different kinetic models (Langmuir, Freundlich and Langmuir – Freundlich) were then used to fit the data, and the model parameters are presented in Table 2.

The Langmuir and Langmuir – Freundlich models fitted better the data for both resins ($R^2 > 0.9$), compared to the Freundlich model ($R^2 = 0.80$). The Langmuir – Freundlich model showed better fit than the Langmuir model for both the Amberlite® IRA67 ($R^2 = 0.94$) and the Diaion® WA30 resin ($R^2 = 0.965$). In the Langmuir model, it is assumed that the adsorption of a given adsorbate occurs as a monolayer sorption onto the surface of a resin containing a finite number of identical binding sites. The adsorbent has uniform binding sites and the adsorbate will only bind to the binding site [32, 39]. In the Freundlich model, it is assumed that the binding of the adsorbate molecules onto the adsorbent is at infinite capacity. The adsorption is not uniform and can occur in a multilayer, with the binding site that has stronger bond energy being occupied first [39]. In the present study, the adsorption capacity of the resin was specific due to the strong interactions between lactic acid and the functional groups present in the Cl⁻ form of the resin. As a result, the Freundlich model did not fit as well as the other models the

kinetic data. According to Sala et al. [32], the Langmuir-Freundlich model is the simple generalisation of both isotherms, modelling the adsorption cooperativity of the two different binding mechanisms. This level of cooperativity can be determined from the nLF value, where, when $nLF > 1$, a positive cooperativity is indicated. When $0 < nLF < 1$, a negative cooperativity in binding process is indicated, whereas when nFL value = 1, it is assumed that the adsorption is purely independent, and no interaction takes place between absorbents. In this study, the nFL values for both resins were > 1 , with 1.96 for Amberlite® IRA67 and 1.83 for Diaion® WA30, indicating a positive cooperativity of the two binding mechanisms.

The maximum binding capacity of a resin (q_{max}) can also be predicted from the Langmuir and Langmuir–Freundlich models, however it cannot be obtained from the Freundlich model as this model assumes that lactic acid binding to the resin is unlimited. The highest q_{max} values for Amberlite® IRA67 were 162.09 and 136.11 mg/g resin based on the Langmuir and Langmuir–Freundlich models, respectively. This value, however, was lower than the q_{max} value reported by Garrett et al. [40], i.e. 203 mg/g of resin, as predicted by the Langmuir model.

3.1.2 Effect of HCl strength on the recovery of lactic acid

The strength of the eluent on the recovery of lactic acid plays a key role for ensuring that all of the lactic acid that is bound to the resin is detached. In this study, HCl was used as an eluent to recover lactic acid from Amberlite® IRA67, which was deemed from the previous work to be the most suitable resin. Figure 8 depicts the elution profiles of lactic acid at different HCl concentrations. At 0.05 M and 0.1 M HCl, only 5.1 and 22.1% lactic acid was recovered from Amberlite® IRA67, respectively. However, at 0.5 and 1.0 M, ~ 96% and 100% recovery of lactic acid was achieved, respectively, indicating that the strength of the eluent plays critical

role for the detachment of lactic acid from the resin. Based on these results, 0.5 M HCl was selected to recover lactic acid in subsequent experiments.

3.2 Separation and purification of D-lactic acid from fermentation broth

3.2.1 Colour removal by activated carbon

After determining the conditions leading to maximum lactic acid adsorption and recovery using the Amberlite® IRA67 resin, the aim was to purify lactic acid from fermentation broths of *L. coryniformis* subsp. *torquens*, where DDGS hydrolysate was used as the fermentation medium. Fermentation broths usually contain besides the component of interest, residual sugars and proteins, as well as by-products of the fermentation process. In this particular case, fermented DDGS hydrolysate contained residual sugars (xylotriose, xylobiose, xylose, arabinose), organic nitrogen in the form of proteins, peptides or amino acids, polyphenols and acetic acid, all of which can contributed into the dark brown colour of the fermentation broth [41]. It is likely that a significant proportion of the dark brown colour of the medium is due to the dark colour of DDGS generated during the drum drying step in the DDGS production process. Therefore, prior to ion exchange purification, the fermented DDGS hydrolysate was initially subjected to activated carbon treatment. Figure 9 shows the effect of various activated carbon concentrations on the colour of the fermentation broth. A positive correlation can be observed as the activated carbon concentrations increased up to 5% (w/v) and the colour of the fermentation broths became notably lighter. For higher activated carbon concentrations (7 and 10%, w/v) no significant changes in colour were observed.

The effect of activated carbon concentration on the recovery of D-lactic acid, protein, oligosaccharides and monosaccharides is shown in Table 3. The recovery of D-lactic acid gradually decreased as the concentration of activated carbon increased. More specifically at 1,

5, 7 and 10% (w/v) of activated carbon, 95, 90, 88 and 85% lactic acid was recovered from the fermentation broth, respectively. A relatively small reduction in monosaccharides and proteins concentrations was overall noted (< 30% removal) when the fermentation broth was treated with activated carbon, even as high as 10% (w/v). Stone and Kozlov [42] reported that activated carbon can only adsorb low molecular weight proteins, in which is in line with protein removal data obtained in this study. On the other hand, oligosaccharides (xylotriose and xylobiose) were completely removed at 7% (w/v) activated carbon. According to Boon et al. [43], activated carbon has higher affinity for trisaccharides and disaccharides compared to monosaccharides with a capacity of 133 mg/g and 117 mg/g of activated carbon, respectively. Based on the above, 7% (w/v) activated carbon was selected as the best concentration to treat the fermentation broth to ensure a satisfactory recovery of lactic acid and at the same time the removal of oligosaccharides and partially of proteins and monosaccharides.

3.2.2 Acidification of fermentation broth by cation exchange chromatography

In lactic acid fermentations, the pH of the culture is normally controlled to prevent microbial growth inhibition and ensure an adequate growth of lactic acid bacteria by the addition of bases ($\text{Ca}(\text{OH})_2$, NH_4OH , NaOH) [44]. As such, the precipitation of metal cation by strong mineral acid is the most common downstream processing option. When $\text{Ca}(\text{OH})_2$ is used as a neutraliser, the fermentation liquid is heated to dissolve all calcium lactate and treated with stoichiometric amounts of sulfuric acid to release free lactic acid. However, this approach requires substantial amounts of sulfuric acid and more importantly, it leads to the production of notable amounts of gypsum that is associated with waste treatment issues [45]. NaOH can be alternatively selected as neutralising agent because of its low cost and the fact that no gypsum is generated as a by-product [45]. As a result, sodium lactate is formed in the fermentation broth. In order to recover lactic acid by anion exchange chromatography, the pH

of the broth needs to be reduced to below pH 3 in order for lactic acid to be in its undissociated form rather than in the form of salt. To achieve this and taking into account that the pH of the fermentation broth used in this study was ~5.5, the fermentation broth was passed through the Amberlite® IRA120 (H⁺) cation exchange resin, in order to exchange the sodium ions and release lactate ions into the solution. Figure 10a depicts the compositional profile of the solution during passing through the resin.

In cation exchange chromatography, no eluent is needed as lactic acid does not bind to Amberlite IRA® 120 (H⁺). Amberlite IRA® 120 is a strong acidic cation exchange resin that contains sulfonic acid functional groups. It is assumed that the hydrogen ions (H⁺) that are attached to the resin's functional group will bind to sodium lactate and convert it to lactic acid in the solution. At the same time, the cation of the lactate salt (Na⁺) will be transferred to the cation exchange resin and transformed through the reaction: $P-H^+ + Na^+La^- \rightarrow P-Na^+ + H^+La^-$, where P is the polymer matrix [46]. In the first 12 ml of the fractions collected, no organic acids and sugars were detected and the pH of the collected fraction was around 6.5, indicating that the fraction contained only water (already present in the column). The pH of the solution then dropped sharply and when it reached ~2.3, the presence of D-lactic acid and other compounds such as acetic acid, xylose and arabinose were detected. The pH of eluate in the collected fraction dropped further with time, to ~1.5, indicating that sodium lactate was successfully converted to undissociated lactic acid. Fractions that had pH below 3 were then pooled together yielding a fraction with a pH of 1.67.

3.2.3 Recovery of D-lactic acid by anion exchange chromatography resin

The undissociated form of D-lactic acid collected from Amberlite® IRA120 (H⁺) was then subjected to Amberlite® IRA67 (Cl⁻). According to Bishai et al. [16], Amberlite® IRA67

has significant commercial potential as it is a robust resin where the amines present in the functional group do not easily detach from the polymer matrix, it is easy to regenerate, and provides higher recovery of lactic acid compared to other resins. The results from this study (Figure 10b) show that during the binding stage, no lactic acid was present in the collected fraction, while other compounds such as xylose and arabinose were detected. The pH of the effluent collected during the binding stage was around 5.5 to 6.0, indicating that the organic acids present in the fermentation broth (lactic acid and acetic acid) were adsorbed to the resin. After washing the column with water, lactic acid was desorbed with 0.5 M HCl. The first acid to be eluted was acetic acid, followed by lactic acid. Fractions that contained only lactic acid were pooled together.

Table 4 presents the recovery and purity of D-lactic acid, as well as the percentage of total sugars and protein removal after each stage of the purification process. After the fermentation broth was treated with 7% (w/v) activated carbon, a ~96% recovery of D-lactic acid recovery was observed and a 9.6% increase in D-lactic acid purity, the latter due to the complete removal of oligosaccharides and of 55% of the proteins that were initially present in the fermentation broth. During the cation exchange stage, a ~93% recovery of D-lactic acid compared to the D-lactic acid concentration in the fermentation broth was observed, and although only 1% increase in D-lactic acid purity was detected, ~21% of total sugar and ~44% of proteins were successfully removed at this stage. Cation exchange did not increase the D-lactic acid purity as its main objective was to acidify the fermentation broth. During the anion exchange step a ~80.4% recovery of D-lactic acid was observed, while 74% of the sugars were removed, leading to a cumulative sugar removal of 100%. As a consequence, the purity of D-lactic acid in the eluent was significantly increased during this step, reaching 91.8%, with the remaining components consisting most likely of small amounts of organic molecules, e.g. proteins, acetic acid and other microbial metabolites. Optical purity values for D-lactic above

92% acid are considered appropriate for the synthesis of PLA [44] and demonstrate that the proposed multi-step downstream process has significant potential for scaling up and commercialisation.

3.3 PDLA synthesis

The azeotropic dehydration polycondensation method was employed using toluene as solvent and tin (II)-2-ethylhexanoate (stannous octoate) as catalyst during polymerisation of D-lactic acid obtained from microbial fermentation of DDGS. Tin compounds and protonic acid have been found to be the best catalysts for the direct polycondensation of high molecular weight PLA [27]. However, stannous octoate is preferable as it is approved by U. S. Food and Drug Administration (FDA) in the list of Indirect Additives used in Food Contact Substances under the Code of Federal Regulation, Title 21 (Food and Drugs). In addition to that, the removal of water is crucial in the direct polycondensation process, as its presence could initiate transesterification reactions or chain terminating reactions of the PLA produced [26, 47]. During azeotropic polycondensation, the water that was present in the feedstock (D-lactic acid) or generated during the polymerisation process was continuously distilled off from the reaction mixture through the Dean-stark trapped apparatus.

After 80 h of polymerisation, a solid yellowish crystal PDLA was produced with an average molecular weight of 3010 Da with a PDI of 4.1, categorised as low molecular weight PLA. In contrast, Kim and Woo [48] produced ten times higher molecular weight of PLLA (33000 Da) after 72 h reaction when the same polycondensation method was used. A similar finding was reported by Marques et al. [49], where 80,000 Da molecular weight of PLLA was produced after 70 h of polymer synthesis. The differences in the molecular weight produced in both cases might be due to the differences in the type of catalyst (tin (II) chloride dihydrate)

and solvent (*m*-xylene with higher than toluene by 29°C boiling point) used during the polymerisation process in those cases. Moreover, other factors such as the purity of D-lactic acid, minute amounts of carboxylic acids like acetic acid, the presence of small amounts water during the polymerisation process and the reaction temperature might also have contributed to the generation of low molecular weight PDLA [12]. **Error! Reference source not found.** compares the molecular weight of PLA produced from this and other studies, where various synthesis methods, monomers (D- or L- lactic acid) and catalysts were employed.

This is the first work demonstrating the synthesis of D-lactic acid polymer (PDLA) employing either a direct method or a one-step polymerisation (azeotropic polycondensation) process. **Pivsa-Art et al. [50]** synthesised PDLA via a two-step polycondensation process, which included a melt polymerisation step followed by solid state polymerisation, and produced PLA with a molecular weight of 33300 Da. A number of interesting applications for low molecular weight PLA have been proposed in various fields, especially in the biomedical [47] and agricultural fields [51]. In the biomedical field, low molecular weight PLA is used as particles for parental controlled drug release in the human body in the form of microspheres, microcapsules, pellets or tablets. Using this approach, drugs are fabricated in a polymeric device (PLA) and the release of the drug is regulated by either diffusion through the polymer barrier or erosion of the polymer matrix [52]. PLA is preferable compared to other polymers such as polyethylene and silicon rubber, as it does not require surgical retrieval, due to its natural degradation in the body. PLA is degraded by simple non-enzymatic hydrolysis (after exposure to moisture) to its monomer (lactic acid) , which can be metabolised by the human body [47]. Drug delivery using low molecular weight PLA offers advantages over high molecular weight PLA as it has a weak retarding effect. Thus, the risk of material accumulation in tissues is reduced as PLA is relatively fast degraded to lactic acid [53].

The same mode of application (controlled release) is also being used in the agricultural field, specifically the agrochemical sector, where PLA can serve as carrier for herbicides and pesticides that are released into the soil. The advantages of using low molecular weight PLA have been demonstrated by Zhao and Wilkins [51], where delayed release of pesticides was observed in the early stages of application, which makes it desirable for sensitive targets such as seed treatment. In their study, bromacil (pesticide) was incorporated into PLA in the form of granules and films, and the delayed release of bromacil was achieved via degradation and erosion of PLA. Since the degraded monomer (lactic acid) is safe and widely distributed in nature, the environmental problems of polymer disposal can be avoided through this approach [6, 51].

In addition, Quynh et al. [54] successfully produced PLA with high thermostability when commercial PLLA polymer (10400 Da) was crosslinked with low molecular weight PDLA (9830 Da). The stereo complex formation of PLLA and PDLA was achieved via the melt polycondensation process and increased the melting temperature of PLA from 175.6 °C to 218.1 °C. This finding has widespread the application of PLA in other areas such as in the production of computer casings, automotive components and heat resistant food packaging [2].

4. Conclusions

Low molecular weight PDLA (3010 Da) was produced via single step azeotropic polycondensation process from purified D-lactic acid originated from DDGS. The developed downstream process reduced effectively the dark colour of fermentation broth, removed oligosaccharides and converted sodium lactate to undissociated lactic acid. At the end of the purification process, approximately 80.4% D-lactic acid was recovered with 91.8% purity. This

study demonstrated that agricultural **residues**, such as DDGS, hold potential as starting materials for biopolymer production.

Acknowledgements

The authors would like to acknowledge the Ministry of Education Malaysia (MOE) and the Universiti Kebangsaan Malaysia, Bangi (UKM), for providing a doctoral sponsorship and financial support to carry out this research.

References

- [1] M. Hans, H. Keul, M. Moeller, Ring-Opening Polymerization of DD-Lactide Catalyzed by Novozyme 435, *Macromol. Biosci.* 9 (2009) 239-247.
- [2] L.T. Sin, A.R. Rahmat, W.A.W.A. Rahman, 1 - Overview of Poly(lactic Acid), *Poly(lactic Acid)*, William Andrew Publishing, Oxford, 2013, pp. 1-70.
- [3] C. Ingrao, C. Tricase, A. Cholewa-Wójcik, A. Kawecka, R. Rana, V. Siracusa, Poly(lactic acid) trays for fresh-food packaging: A Carbon Footprint assessment, *Sci. Total Environ.* (2015) 385-398.
- [4] NatureWorks LLC, Ingeo in use, NatureWorks LLC, 2017.
- [5] IHS Markit, Lactic Acid, Its Salts and Esters, 2015.
- [6] M. Jamshidian, E.A. Tehrany, M. Imran, M. Jacquot, S. Desobry, Poly-lactic acid: Production, applications, nanocomposites, and release studies, *Compr. Rev. Food Sci. Food Saf.* 9 (2010) 552-571.
- [7] I.S. Tawakkal, M.J. Cran, J. Miltz, S.W. Bigger, A Review of Poly (Lactic Acid)-Based Materials for Antimicrobial Packaging, *J. Food Sci.* 79 (2014).

548 [8] Z. Bai, Z. Gao, B. He, B. Wu, Effect of lignocellulose-derived inhibitors on the growth and
 549 d-lactic acid production of *Sporolactobacillus inulinus* YBS1-5, Bioprocess. Biosyst. Eng. 38
 550 (2015) 1993-2001.

551 [9] T. Tanaka, M. Hoshina, S. Tanabe, K. Sakai, S. Ohtsubo, M. Taniguchi, Production of D-
 552 lactic acid from defatted rice bran by simultaneous saccharification and fermentation,
 553 Bioresour. Technol. 97 (2006) 211-217.

554 [10] M. Othman, A.B. Ariff, L. Rios-Solis, M. Halim, Extractive Fermentation of Lactic Acid
 555 in Lactic Acid Bacteria Cultivation: A Review, Front. Microbiol. 8 (2017) 2285-2285.

556 [11] N. Pradhan, E. Rene, P. Lens, L. Dipasquale, G. D'Ippolito, A. Fontana, A. Panico, G.
 557 Esposito, Adsorption Behaviour of Lactic Acid on Granular Activated Carbon and Anionic
 558 Resins: Thermodynamics, Isotherms and Kinetic Studies, Energies. 10 (2017) 665.

559 [12] S. Inkinen, M. Hakkarainen, A.-C. Albertsson, A. Södergård, From Lactic Acid to
 560 Poly(lactic acid) (PLA): Characterization and Analysis of PLA and Its Precursors,
 561 Biomacromolecules. 12 (2011) 523-532.

562 [13] V.S. Kislik, Chapter 2 - Principles of Solvent Extraction of Organic and Mineral Acids,
 563 Solvent Extraction, Elsevier, Amsterdam, 2012, pp. 69-111.

564 [14] Q.Z. Li, X.L. Jiang, X.J. Feng, J.M. Wang, C. Sun, H.B. Zhang, M. Xian, H.Z. Liu,
 565 Recovery Processes of Organic Acids from Fermentation Broths in the Biomass-Based
 566 Industry, J. Microbiol. Biotechnol. 26 (2016) 1-8.

567 [15] A. Komesu, M.R.W. Maciel, R. Maciel Filho, Separation and Purification Technologies
 568 for Lactic Acid—A Brief Review, BioResources 12 (2017) 6885-6901.

569 [16] M. Bishai, S. De, B. Adhikari, R. Banerjee, A platform technology of recovery of lactic
 570 acid from a fermentation broth of novel substrate *Zizyphus oenophlia*, 3 Biotech 5 (2015) 455-
 571 463.

572 [17] R.P. John, K.M. Nampoothiri, A. Pandey, L (+)-Lactic acid recovery from cassava bagasse
573 based fermented medium using anion exchange resins, *Braz. Arch. Biol. Technol.* 51 (2008)
574 1241-1248.

575 [18] W.-Y. Tong, X.-Y. Fu, S.-M. Lee, J. Yu, J.-W. Liu, D.-Z. Wei, Y.-M. Koo, Purification
576 of L (+)-lactic acid from fermentation broth with paper sludge as a cellulosic feedstock using
577 weak anion exchanger Amberlite IRA-92, *Biochem. Eng. J.* 18 (2004) 89-96.

578 [19] N. Murali, K. Srinivas, B.K. Ahring, Biochemical Production and Separation of
579 Carboxylic Acids for Biorefinery Applications, *Fermentation.* 3 (2017) 22.

580 [20] S. Kulprathipanja, A.R. Oroskar, Separation of lactic acid from fermentation broth with
581 an anionic polymeric absorbent, Google Patents, 1991.

582 [21] R.L. Evangelista, Z.L. Nikolov, Recovery and Purification of Lactic Acid from
583 Fermentation Broth by Adsorption, in: C.E. Wyman, B.H. Davison (Eds.) *Seventeenth*
584 *Symposium on Biotechnology for Fuels and Chemicals: Presented as Volumes 57 and 58 of*
585 *Applied Biochemistry and Biotechnology*, Humana Press, Totowa, NJ, 1996, pp. 471-480.

586 [22] M.I. González, S. Álvarez, F.A. Riera, R. Álvarez, Purification of lactic acid from
587 fermentation broths by ion-exchange resins, *Ind. Eng. Chem. Res.* 45 (2006) 3243-3247.

588 [23] E.T.H. Vink, K.R. Rábago, D.A. Glassner, P.R. Gruber, Applications of life cycle
589 assessment to NatureWorks™ polylactide (PLA) production, *Polym. Degrad. Stab.* 80 (2003)
590 403-419.

591 [24] Corbion N.V., PLA polymers, Corbion N.V., 2017.

592 [25] L. Xiao, B. Wang, G. Yang, M. Gauthier, Poly (lactic acid)-based biomaterials: synthesis,
593 modification and applications, *Biomedical Science, Engineering and Technology*,
594 InTech2012.

595 [26] A. Södergård, S. Inkinen, Production, chemistry and properties of polylactides,
596 Biopolymers-New Materials for Sustainable Films and Coatings (2011) 43-63.

597 [27] M. Ajioka, K. Enomoto, K. Suzuki, A. Yamaguchi, The basic properties of poly(lactic
598 acid) produced by the direct condensation polymerization of lactic acid, J. Environ. Polym.
599 Degrad. 3 (1995) 225-234.

600 [28] N.A.M. Zaini, A. Chatzifragkou, D. Charalampopoulos, Microbial production of D-lactic
601 acid from Dried Distillers Grains with Solubles (DDGS), Eng. Life Sci. 19 (2019) 21 - 30.

602 [29] A. Moldes, J. Alonso, J. Parajo, Recovery of lactic acid from simultaneous saccharification
603 and fermentation media using anion exchange resins, Bioprocess. Biosyst. Eng. 25 (2003) 357-
604 363.

605 [30] The Dow Chemical Company, DOW Ion Exchange Resins - Pre-use Preparation - Resin
606 for industrial use, 2017.

607 [31] M.P. Bernardo, L.F. Coelho, D.C. Sass, J. Contiero, L-(+)-Lactic acid production by
608 *Lactobacillus rhamnosus* B103 from dairy industry waste, Braz. J. Microbiol. 47 (2016) 640-
609 646.

610 [32] L. Sala, F.S. Figueira, G.P. Cerveira, C.C. Moraes, S.J. Kalil, Kinetics and adsorption
611 isotherm of C-phycocyanin from *Spirulina platensis* on ion-exchange resins, Braz. J. Chem.
612 Eng. 31 (2014) 1013-1022.

613 [33] S.M. Beitel, D.C. Sass, L.F. Coelho, J. Contiero, High D (–) lactic acid levels production
614 by *Sporolactobacillus nakayamae* and an efficient purification, Ann. Microbiol. 66 (2016)
615 1367-1376.

616 [34] S. Lie, The EBC-Ninhydrin method for determination of free alpha amino nitrogen, J. I.
617 Brewing 79 (1973) 37-41.

618 [35] A. Yousuf, F. Bonk, J.-R. Bastidas-Oyanedel, J.E. Schmidt, Recovery of carboxylic acids
 619 produced during dark fermentation of food waste by adsorption on Amberlite IRA-67 and
 620 activated carbon, *Bioresour. Technol.* 217 (2016) 137-140.

621 [36] N. Syzova, A.M. Eyal, A. Vitner, B. Hazan, Extraction of Carboxylic Acids by ABC
 622 Extractants: Effects of Temperature, the Polarity of the Diluent, and the Ratio Between
 623 Extractant Components, *Solvent Extr. Ion Exc.* 22 (2004) 69-88.

624 [37] S.K. Niazi, J.L. Brown, *Fundamentals of Modern Bioprocessing*, CRC Press, Boca Raton,
 625 FL, 2016.

626 [38] Saeeduddin, A. Khanzada, Dissociation constant studies of lactic acid at different
 627 temperatures and in mixed organic-water solvent systems, *J. Chem. Soc. Pakistan* 26 (2004)
 628 23-27.

629 [39] K.Y. Foo, B.H. Hameed, Insights into the modeling of adsorption isotherm systems,
 630 *Chem. Eng. J.* 156 (2010) 2-10.

631 [40] B.G. Garrett, K. Srinivas, B.K. Ahring, Performance and stability of Amberlite™ IRA-67
 632 ion exchange resin for product extraction and pH control during homolactic fermentation of
 633 corn stover sugars, *Biochem. Eng. J.* 94 (2015) 1-8.

634 [41] T. Qin, M. Song, K. Jiang, J. Zhou, W. Zhuang, Y. Chen, D. Liu, X. Chen, H. Ying, J.
 635 Wu, Efficient decolorization of citric acid fermentation broth using carbon materials prepared
 636 from phosphoric acid activation of hydrothermally treated corncob, *RSC Advances* 7 (2017)
 637 37112-37121.

638 [42] M.T. Stone, M. Kozlov, Separating proteins with activated carbon, *Langmuir* 30 (2014)
 639 8046-8055.

640 [43] M. Boon, K. Van't Riet, A. Janssen, Enzymatic synthesis of oligosaccharides: product
 641 removal during a kinetically controlled reaction, *Biotechnol. Bioeng.* 70 (2000) 411-420.

642 [44] C.M. Nguyen, G.J. Choi, Y.H. Choi, K.S. Jang, J.-C. Kim, d- and l-lactic acid production
 643 from fresh sweet potato through simultaneous saccharification and fermentation, *Biochem.*
 644 *Eng. J.* 81 (2013) 40-46.

645 [45] K. Wang, W. Li, Y. Fan, W. Xing, Integrated membrane process for the purification of
 646 lactic acid from a fermentation broth neutralized with sodium hydroxide, *Ind. Eng. Chem. Res.*
 647 52 (2013) 2412-2417.

648 [46] A.M. Eyal, P. Elankovan, Process for the recovery of lactic acid from aqueous lactate salt
 649 solutions, involving the use of ion exchangers, Google Patents, 2007.

650 [47] C.S. Proikakis, P.A. Tarantili, A.G. Andreopoulos, Synthesis and Characterization of Low
 651 Molecular Weight Polylactic Acid, *J. Elastom. Plast.* 34 (2002) 49-63.

652 [48] K.W. Kim, S.I. Woo, Synthesis of High-Molecular-Weight Poly (L-lactic acid) by Direct
 653 Polycondensation, *Macromol. Chem. Phys.* 203 (2002) 2245-2250.

654 [49] D. Marques, S. Jarmelo, C. M. S. G. Baptista, H. Gil, Poly(lactic acid) Synthesis in
 655 Solution Polymerization, *Macromol. Symp.* 296 (2010) 63-71.

656 [50] S. Pivsa-Art, T. Tong-ngok, S. Junngam, R. Wongpajan, W. Pivsa-Art, Synthesis of
 657 Poly(D-Lactic Acid) Using a 2-Steps Direct Polycondensation Process, *Energy Procedia.* 34
 658 (2013) 604-609.

659 [51] J. Zhao, R.M. Wilkins, Low Molecular Weight Polylactic Acid as a Matrix for the Delayed
 660 Release of Pesticides, *J. Agric. Food Chem.* 53 (2005) 4076-4082.

661 [52] R. Jalil, J.R. Nixon, Biodegradable poly(lactic acid) and poly(lactide-co-glycolide)
 662 microcapsules: problems associated with preparative techniques and release properties, *J.*
 663 *Microencapsul.* 7 (1990) 297-325.

664 [53] M.S. Lopes, A.L. Jardini, R.M. Filho, Poly (Lactic Acid) Production for Tissue
 665 Engineering Applications, *Procedia Eng.* 42 (2012) 1402-1413.

666 [54] T.M. Quynh, H. Mitomo, M. Yoneyama, N.Q. Hien, Properties of radiation-induced
 667 crosslinking stereocomplexes derived from poly(L-lactide) and different poly(D-lactide),
 668 *Polym. Eng. Sci.* 49 (2009) 970-976.

669 [55] F. Achmad, K. Yamane, S. Quan, T. Kokugan, Synthesis of polylactic acid by direct
 670 polycondensation under vacuum without catalysts, solvents and initiators, *Chem. Eng. J.* 151
 671 (2009) 342-350.

672 [56] S.H. Kim, Y.H. Kim, Direct condensation polymerization of lactic acid, *Macromol.*
 673 *Symp.*, Wiley Online Library, 1999, pp. 277-287.

674 [57] Y. Zhao, Z. Wang, J. Wang, H. Mai, B. Yan, F. Yang, Direct synthesis of poly(D,L-lactic
 675 acid) by melt polycondensation and its application in drug delivery, *J. Appl. Polym. Sci.* 91
 676 (2004) 2143-2150.

677 [58] W. Huang, N. Cheng, Y. Qi, T. Zhang, W. Jiang, H. Li, Q. Zhang, Synthesis of high
 678 molecular weight poly(l-lactic acid) and poly(d-lactic acid) with improved thermal stability via
 679 melt/solid polycondensation catalyzed by biogenic creatinine, *Polymer* 55 (2014) 1491-1496.

680 [59] C. Liu, Y. Jia, A. He, Preparation of Higher Molecular Weight Poly (L-lactic Acid) by
 681 Chain Extension, *Int. J. Polym. Sci.* 2013 (2013) 6.

682 [60] V. Lassalle, M.L. Ferreira, Lipase-catalyzed synthesis of polylactic acid: an overview of
 683 the experimental aspects, *J. Chem. Technol. Biotechnol.* 83 (2008) 1493-1502.

684 [61] C. Chuensangjun, C. Pechyen, Y. Chisti, S. Sirisansaneeyakul, Lipase-catalysed
 685 polymerization of lactic acid and the properties of the polymer, *Advanced Materials Research*,
 686 *Trans Tech Publ*, 2012, pp. 154-157.

687

688

689 Figure Captions

690 Figure 1: Effect of (a) pH and (b) temperature on lactic acid binding by four anionic resins

691

692 Figure 2: Adsorption isotherms of lactic acid to (a) Amberlite® IRA67 and (b) Diaion®

693 WA30 at 25°C; - - - Langmuir model, Freundlich model, ____ Langmuir-Freundlich

694 model

695

696 Figure 3: Elution profiles of lactic acid from the Amberlite® IRA67 resin (saturated with 20 ml

697 of 30 g/l lactic acid) at different concentrations of HCl at 25°C; (—●—) 0.05M, (—▲—) 0.1M HCl,

698 (—■—) 0.5M HCl and (—×—) 1.0M HCl.

699

700 Figure 4: Samples of fermentation broth treated with different concentrations of activated

701 carbon at 25 °C for 1.5 h

702

703 Figure 5: Elution profile of fermentation broth on (a) cation exchange chromatography with

704 Amberlite IRA120 (H⁺) resin and (b) adsorption and elution profile of fermentation broth

705 during anion exchange chromatography with Amberlite® IRA67 (Cl⁻) resin

706

707

708

709

710

711

712 Table 1: Properties of ion exchange resins (information provided by Sigma-Aldrich, US)

Ion exchange type	Resin	Strength	Particle size (µm)	Matrix	Active functional group	pH
Anion	Amberlite® IRA67	Weak basicity	500-750	Acrylic (gel)	Tertiary amine	0 - 7
Anion	Diaion® WA30	Weak basicity	680	Styrene-divinylbenzene (highly porous)	Tertiary amine	0 - 9
Anion	Amberlite® IRA400	Strong basicity	600-750	Styrene-divinylbenzene (gel)	Quaternary ammonium	0 - 14
Anion	Dowex® Marathon™ MSA	Strong basicity	640	Styrene-divinylbenzene (macroporous)	Quaternary ammonium	0 - 14
Cation	Amberlite® IRA120	Strong acidity	620-830	Styrene-divinylbenzene (gel)	Sulfonic acid	0 - 14

713

714

715

716

717

718

719

720

721

722

723

724

Table 2: Langmuir, Freundlich and Langmuir – Freundlich isotherm parameters describing the adsorption of lactic acid to Amberlite® IRA67 and Diaion® WA30

Model	Parameter	Amberlite® IRA67	Diaion® WA30
Langmuir	q_{max} (mg/g)	162.09	102.47
	K	0.0096	0.019
	R^2	0.910	0.940
Freundlich	K_f	10.88	13.379
	n	2.475	3.200
	R^2	0.801	0.800
Langmuir-Freundlich	q_{max} (mg/g)	136.11	91.51
	K_{LF}	0.0002	0.001
	n_{LF}	1.96	1.83
	R^2	0.940	0.965

739 Table 3: Recovery of D-lactic acid, **free amino nitrogen**, oligosaccharides and
740 monosaccharides after treatment with activated carbon at different concentrations

Activated carbon (%, w/v)	*Recovery (%)					
	D-lactic acid	Free amino nitrogen	Oligosaccharides		Monosaccharides	
			Xylotriose	Xylobiose	Xylose	Arabinose
0	100 ± 0.0	100 ± 2.5	100 ± 0.0	100 ± 0.0	100 ± 0.0	100 ± 0.0
1	95 ± 0.4	94.0 ± 0.2	77.4 ± 0.5	87.6 ± 0.0	90.4 ± 0.9	83.4 ± 1.6
5	90 ± 0.3	83.6 ± 1.3	0	42.8 ± 1.0	85.7 ± 0.6	79.9 ± 0.9
7	88 ± 3.4	83.0 ± 1.2	0	0	82.2 ± 3.0	76.7 ± 2.7
10	85 ± 1.9	80.2 ± 2.8	0	0	72.7 ± 1.7	70.0 ± 1.4

741 *Initial concentration in the fermentation broth: D- lactic acid, 25.9 g/l; xylotriose, 1.0 g/l; xylobiose,
742 3.8 g/l; xylose, 4.8 g/l; arabinose, 0.5 g/l and **free amino nitrogen**, 152.8 mg/l

743

744

745

746

747

748

749 Table 4: Recovery and purity of D-lactic acid from the fermentation broth during the different downstream processing stages

Purification stages	Volume (ml)	D-lactic Acid			Total Oligosaccharides		Total Monosaccharides		Free amino nitrogen	
		g/l	Recovery (%)	Purity* (%)	g/l	Cumulative removal (%)	g/l	Cumulative removal (%)	mg/l	Cumulative removal (%)
Fermentation broth	50	25.9	100	54.6	4.5	0	5.3	0	152.8	0
7% Activated carbon	92	13.5	95.9	64.2	0	100	2.7	4.5	37.8	55
Cation exchange chromatography (Amberlite® IRA120, H ⁺)	132	9.1	92.5	65.2	0	100	1.7	26.2	0.6	99
Anion exchange chromatography (Amberlite® IRA67, Cl ⁻)	29	36.0	80.4	91.8	0	100	0	100	0.4	99

750 *The purity (%) of lactic acid in the eluate was determined according to Equation

751 Table 5: Comparisons of molecular weight of PLA produced form this and other studies,
752 using different synthesis methods, catalysts and monomers were.

Method	Lactic acid form	Catalyst	Polymer	Molecular weight (Da)	Reference
Azeotropic polycondensation	D	Tin (II)-2-ethylhexanoate, $\text{SnC}_{16}\text{H}_{30}\text{O}_4$	PDLA	3010	This study
	L	Tin (II) chloride dihydrate, $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$	PLLA	33000	[48]
	L	Tin (II) chloride dihydrate, $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$	PLLA	80000	[49]
Direct polycondensation	L	-	PLLA	90000	[55]
	L	Antimony trioxide, Sb_2O_3	PLLA	67000	[56]
Melt polymerisation	DL	Tin (II) chloride, SnCl_2	PDLLA	4100	[57]
1.Solid state polymerisation (SSP)	L	Creatinine, CR	PLLA	120000	[58]
2.Melt polymerisation					
1. Melt polymerisation	D	2-Naphthalenesulfonic acid (2-NSA)	PDLA	33300	[50]
2. Solid state polymerisation (SSP)					
1.Ring opening polymerisation (ROP)	L	1.Tin (II)-2-ethylhexanoate, $\text{C}_{16}\text{H}_{30}\text{O}_4\text{Sn}$	PLLA	203000	[59]
2.Chain extension		2.Hexamethylene diisocyanate, HDI			
Enzymatic polymerisation	DL	-	PDLLA	2400	[60]
	L	-	PLLA	4500	[61]

753


754

755

756

757

(a)



(b)





Figure 6

765

766


(a)



767

768

(b)




769

770

Figure 7

771

772



773

774

Figure 8

775

776

777

778

779

780

781

782

783




Figure 9





Figure 10